



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 1 **Sample #:** 3140 **Placement Date:** 12/16/2024 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 34
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert box at south end **Lat/Long:** 38.9446233 / -104.6091133

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
1	20-00317 136629	10.00	Slump: 4 Spec: 3 - 5	Result: 6.5 Spec.: 5 - 8	137.0	71	34

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
1 / 10893	7	12/23/2024	4780	Type 2
1 / 10894	28	01/13/2025	6340	Type 3
1 / 10895	28	01/13/2025	6170	Type 5
1 / 10896	28	01/13/2025	6200	Type 3

Average Strength (psi): 7 Day - 4780 psi, 28 Day - 6240 psi

01/13/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 2 **Sample #:** 3234 **Placement Date:** 01/02/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 41
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert footing, 90' N from south end **Lat/Long:** 38.9440067 / -104.6075046

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
2	20-00317 138144	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	136.8	80	41

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
2 / 11178	7	01/09/2025	4460	Type 2
2 / 11179	28	01/30/2025	5410	Type 2
2 / 11180	28	01/30/2025	5350	Type 2
2 / 11181	28	01/30/2025	5590	Type 3

Average Strength (psi): 7 Day - 4460 psi, 28 Day - 5450 psi

01/31/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 3 **Sample #:** 3237 **Placement Date:** 01/02/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 43
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert footing, 30' from North end

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
3	20-00317 138180	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 5.5 Spec.: 5 - 8	138.7	80	43

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
3 / 11190	7	01/09/2025	4580	Type 5
3 / 11191	28	01/30/2025	5760	Type 3
3 / 11192	28	01/30/2025	5970	Type 3
3 / 11193	28	01/30/2025	5900	Type 5

Average Strength (psi): 7 Day - 4580 psi, 28 Day - 5880 psi

01/31/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 4 **Sample #:** 3321 **Placement Date:** 01/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 44
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Bridge - Wing Wall **Location Details:** Bridge Foundation wall, 60' South from North end

Notes: Additional trucks tested by Pete Lein QC

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
4	20-00325 139538	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 6.5 Spec.: 5 - 8	140.6	65	44

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
4 / 11403	7	01/31/2025	5710	Type 2
4 / 11404	28	02/21/2025	6900	Type 2
4 / 11405	28	02/21/2025	6700	Type 3
4 / 11406	28	02/21/2025	6700	Type 3

Average Strength (psi): 7 Day - 5710 psi, 28 Day - 6770 psi

02/21/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 5 **Sample #:** 3354 **Placement Date:** 01/31/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 46

Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Building Exterior - Foundation Wall **Location Details:** Culvert East side foundation wall center mass, 150' North from South end

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
5	20-00325 140220	10.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	136.4	74	46

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
5 / 11480	7	02/07/2025	3940	Type 2
5 / 11481	28	02/28/2025	5100	Type 5
5 / 11482	28	02/28/2025	5220	Type 5
5 / 11483	28	02/28/2025	5380	Type 5

Average Strength (psi): 7 Day - 3940 psi, 28 Day - 5230 psi

03/05/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 6 **Sample #:** 3392 **Placement Date:** 02/07/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 59
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Bridge - Wing Wall Footer **Location Details:** Culvert east wall, 50' North from South end **Lat/Long:** 38.9448515 / -104.6096189

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
6	20-00327 140957	10.00	Slump: 4 Spec: 3 - 5	Result: 6.5 Spec.: 5 - 8	139.6	75	59

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
6 / 11645	7	02/14/2025	4490	Type 3
6 / 11646	28	03/07/2025	5590	Type 3
6 / 11647	28	03/07/2025	5350	Type 5
6 / 11648	28	03/07/2025	5760	Type 2

Average Strength (psi): 7 Day - 4490 psi, 28 Day - 5570 psi

03/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 7 **Sample #:** 3454 **Placement Date:** 02/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 56
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top, North end structure **Lat/Long:** 38.9456356 / -104.6094538

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
7	20-00305 141578	10.00	Slump: 3 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	137.1	72	56

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
7 / 11850	3	02/27/2025	3510	Type 3
7 / 11846	7	03/03/2025	4320	Type 2
7 / 11847	28	03/24/2025	5620	Type 2
7 / 11848	28	03/24/2025	5410	Type 2
7 / 11849	28	03/24/2025	5540	Type 2

Average Strength (psi): 3 Day - 3510 psi, 7 Day - 4330 psi, 28 Day - 5520 psi

03/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 8 **Sample #:** 3457 **Placement Date:** 02/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 60
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top 60' from South end **Lat/Long:** 38.9453151 / -104.6092548

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
8	20-02248 141616	10.00	Slump: 5 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	137.1	69	60

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
8 / 11856	3	02/27/2025	3140	Type 3
8 / 11852	7	03/03/2025	3950	Type 3
8 / 11853	28	03/24/2025	5000	Type 3
8 / 11854	28	03/24/2025	4810	Type 2
8 / 11855	28	03/24/2025	5010	Type 2

Average Strength (psi): 3 Day - 3140 psi, 7 Day - 3950 psi, 28 Day - 4940 psi

03/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 9 **Sample #:** 3510 **Placement Date:** 02/28/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 59
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** East culvert wall, 30' from South end **Lat/Long:** 38.9445977 / -104.6092405

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
9	20-00317 142326	9.50	Slump: 4 1/2 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	135.2	75	59

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
9 / 12023	7	03/07/2025	3940	Type 5
9 / 12024	28	03/28/2025	5000	Type 3
9 / 12025	28	03/28/2025	4910	Type 3
9 / 12026	28	03/28/2025	4560	Type 2

Average Strength (psi): 7 Day - 3940 psi, 28 Day - 4820 psi

03/31/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 10 **Sample #:** 3580 **Placement Date:** 03/10/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 58
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top, 80' North from South end **Lat/Long:** 38.944837 / -104.6094741

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
10	20-00330 143098	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	137.1	69	58

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
10 / 12271	7	03/17/2025	4310	Type 3
10 / 12272	28	04/07/2025	5390	Type 5
10 / 12273	28	04/07/2025	5360	Type 2
10 / 12274	28	04/07/2025	5360	Type 3

Average Strength (psi): 7 Day - 4310 psi, 28 Day - 5370 psi

04/07/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 11 **Sample #:** 3582 **Placement Date:** 03/10/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 63
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top, 20' North from South end **Lat/Long:** 38.9448587 / -104.6092407

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
11	20-00317 143138	10.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	136.6	68	63

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
11 / 12277	7	03/17/2025	3780	Type 3
11 / 12278	28	04/07/2025	4910	Type 2
11 / 12279	28	04/07/2025	4670	Type 3
11 / 12280	28	04/07/2025	4850	Type 3

Average Strength (psi): 7 Day - 3780 psi, 28 Day - 4810 psi

04/07/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 12 **Sample #:** 3607 **Placement Date:** 03/12/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 57
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Inlet base at south end of culvert **Lat/Long:** 38.9446975 / -104.6093471

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
12	20-00308 143561	8.75	Slump: 5 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	134.8	75	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
12 / 12380	7	03/19/2025	2920	Type 5
12 / 12381	28	04/09/2025	3530	Type 2
12 / 12382	56	05/07/2025	4400	Type 5
12 / 12383	90	06/10/2025	4810	Type 3

Average Strength (psi): 7 Day - 2920 psi, 28 Day - 3530 psi, 56 Day - 4400 psi, 90 Day - 4810 psi

06/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 13 **Sample #:** 3695 **Placement Date:** 03/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 63
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Bridge - Wing Wall **Location Details:** Wing wall at the southern end of the culvert inlet **Lat/Long:** 38.9440825 / -104.6095857

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
13	20-00325 144669	8.50	Slump: 4 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	135.8	73	63

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
13 / 12666	7	03/31/2025	4130	Type 2
13 / 12667	28	04/21/2025	4910	Type 2
13 / 12668	28	04/21/2025	4920	Type 2
13 / 12669	28	04/21/2025	4820	Type 2

Average Strength (psi): 7 Day - 4130 psi, 28 Day - 4880 psi

04/28/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 14 **Sample #:** 3774 **Placement Date:** 03/31/2025 **Technician:** Michael Crytser **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 49

Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Other **Location Details:** Box culvert forebay walls at the south west corner of the site. **Lat/Long:** 38.9446589 / -104.6093474

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
14	20-00316 145651	8.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	138.0	65	49

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
14 / 12949	7	04/07/2025	4830	Type 2
14 / 12950	28	04/28/2025	5860	Type 2
14 / 12951	28	04/28/2025	5480	Type 2
14 / 12952	28	04/28/2025	5910	Type 3

Average Strength (psi): 7 Day - 4830 psi, 28 Day - 5750 psi

05/05/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 15 **Sample #:** 4023 **Placement Date:** 04/28/2025 **Technician:** Nathan Weaver **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 57
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** At Station 0 + 35 of the Falcon Marketplace Roundabout. **Lat/Long:** 38.9440169 / -104.6112748

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
15	21-02277 149144	10.00	Slump: 4 1/4 Spec: 3 - 5	Result: 5.5 Spec.: 5 - 8	140.0	66	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
15 / 13735	7	05/05/2025	4190	Type 3
15 / 13736	28	05/26/2025	4840	Type 3
15 / 13737	28	05/26/2025	4530	Type 2
15 / 13738	28	05/26/2025	5230	Type 3

Average Strength (psi): 7 Day - 4190 psi, 28 Day - 4870 psi

06/02/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 16 **Sample #:** 4075 **Placement Date:** 05/08/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 48
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Slab on Grade **Location Details:** At Station 10 + 00. **Lat/Long:** 38.9463513 / -104.6093292

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
16	20-00331 150498	10.00	Slump: 5 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	138.0	77	48

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
16 / 13930	7	05/15/2025	3960	Type 2
16 / 13931	28	06/05/2025	5120	Type 2
16 / 13932	28	06/05/2025	5540	Type 2
16 / 13933	28	06/05/2025	5140	Type 2

Average Strength (psi): 7 Day - 3960 psi, 28 Day - 5270 psi

06/07/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 17 **Sample #:** 4078 **Placement Date:** 05/08/2025 **Technician:** Kirby Hooker **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 51
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Interior - Slab on Grade **Location Details:** At Station 7+50. **Lat/Long:** 38.9463316 / -104.6093101

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
17	20-00305 150534	10.00	Slump: 5 Spec: 3 - 5	Result: 6.6 Spec.: 5 - 8	139.2	78	51

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
17 / 13938	7	05/15/2025	4190	Type 3
17 / 13939	28	06/05/2025	5660	Type 2
17 / 13940	28	06/05/2025	5790	Type 2
17 / 13941	28	06/05/2025	5820	Type 3

Average Strength (psi): 7 Day - 4190 psi, 28 Day - 5760 psi

06/07/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 18 **Sample #:** 4166 **Placement Date:** 05/20/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 54
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** At the northwest corner of the culvert. **Lat/Long:** 38.9462047 / -104.6092239

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
18	995 152596	10.00	Slump: 4 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	136.8	74	54

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
18 / 14205	7	05/27/2025	4100	Type 3
18 / 14206	28	06/17/2025	4670	Type 2
18 / 14207	28	06/17/2025	4820	Type 2
18 / 14208	28	06/17/2025	4630	Type 2

Average Strength (psi): 7 Day - 4100 psi, 28 Day - 4710 psi

06/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 19 **Sample #:** 4173 **Placement Date:** 05/20/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 59

Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Inlet Box **Location Details:** From the northeast corner of of Falcon Market Place and Owl Place, 10 feet east and 20 feet south. **Lat/Long:** 38.9463463 / -104.6085667

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
19	20-00311 152651	10.00	Slump: 5 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	139.2	68	59

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
19 / 14217	7	05/27/2025	3990	Type 2
19 / 14218	28	06/17/2025	5660	Type 2
19 / 14219	28	06/17/2025	5390	Type 2
19 / 14220	28	06/17/2025	5440	Type 2

Average Strength (psi): 7 Day - 3990 psi, 28 Day - 5490 psi

06/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 20 **Sample #:** 4259 **Placement Date:** 05/30/2025 **Technician:** Herbert Hafenrichter **Weather Conditions:** Sunny **Air Temp (°F):** 61
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert at the northwest corner of the project. **Lat/Long:** 38.94824173 / -104.60815031

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
20	21-02276 154326	10.00	Slump: 4 Spec: 3 - 5	Result: 7.9 Spec.: 5 - 8	138.0	65	61

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
20 / 14582	7	06/06/2025	3580	Type 3
20 / 14583	28	06/27/2025	5210	Type 3
20 / 14584	28	06/27/2025	4770	Type 2
20 / 14585	28	06/27/2025	4940	Type 2

Average Strength (psi): 7 Day - 3580 psi, 28 Day - 4980 psi

07/07/2025

Reviewed by: Robert Jaquet, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 21 **Sample #:** 4268 **Placement Date:** 05/30/2025 **Technician:** Herbert Hafenrichter **Weather Conditions:** Sunny **Air Temp (°F):** 68
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** From the northwest corner of the site, 30 feet east.

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
21	988 154407	10.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	140.8	70	68

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
21 / 14586	7	06/06/2025	3750	Type 3
21 / 14587	28	06/27/2025	5410	Type 2
21 / 14588	28	06/27/2025	5170	Type 5
21 / 14589	28	06/27/2025	5190	Type 5

Average Strength (psi): 7 Day - 3750 psi, 28 Day - 5260 psi

07/07/2025

Reviewed by: Robert Jaquet, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 22 **Sample #:** 4309 **Placement Date:** 06/09/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 70
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Culvert top, north branch 80' from Meridian Road. **Lat/Long:** 38.9458696 / -104.608054

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
22	21-02295 155816	10.00	Slump: 4 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	138.3	75	70

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
22 / 14620	7	06/16/2025	3820	Type 2
22 / 14621	28	07/07/2025	4740	Type 2
22 / 14622	28	07/07/2025	4870	Type 2
22 / 14623	28	07/07/2025	4860	Type 3

Average Strength (psi): 7 Day - 3820 psi, 28 Day - 4820 psi

07/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 23 **Sample #:** 4332 **Placement Date:** 06/11/2025 **Technician:** Michael Crytser **Weather Conditions:** Sunny **Air Temp (°F):** 80
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** North most Culvert Pad. **Lat/Long:** 38.9465516 / -104.6084235

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
23	21-02272 156397	10.00	Slump: 4 Spec: 3 - 5	Result: 7.8 Spec.: 5 - 8	138.0	85	80

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
23 / 14690	7	06/18/2025	3580	Type 2
23 / 14691	28	07/09/2025	4570	Type 2
23 / 14692	28	07/09/2025	4570	Type 2
23 / 14693	28	07/09/2025	4480	Type 3

Average Strength (psi): 7 Day - 3580 psi, 28 Day - 4540 psi

07/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 24 **Sample #:** 4379 **Placement Date:** 06/18/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 66
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Box Culvert at Station 10+50.

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
24	20-00332 157626	9.00	Slump: 4 Spec: 3 - 5	Result: 7.8 Spec.: 5 - 8	137.2	80	66

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
24 / 14827	8	06/25/2025	3370	Type 2
24 / 14828	28	07/16/2025	3950	Type 3
24 / 14829	56	08/13/2025	5090	Type 5
24 / 14830	56	08/13/2025	5110	Type 3

Average Strength (psi): 8 Day - 3370 psi, 28 Day - 3950 psi, 56 Day - 5100 psi

08/18/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 25 **Sample #:** 4444 **Placement Date:** 06/25/2025 **Technician:** Herbert Hafenrichter **Weather Conditions:** Sunny / Cloudy **Air Temp (°F):** 73
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** From the Northeast corner of the culvert pad. **Lat/Long:** 38.94514973 / -104.60862881

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
25	20-00329 158844	9.25	Slump: 3 Spec: 3 - 5	Result: 6.8 Spec.: 5 - 8	139.2	75	73

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
25 / 14982	7	07/02/2025	3810	Type 5
25 / 14983	28	07/23/2025	5100	Type 3
25 / 14984	28	07/23/2025	5230	Type 2
25 / 14985	28	07/23/2025	5250	Type 3

Average Strength (psi): 7 Day - 3810 psi, 28 Day - 5190 psi

07/25/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 26 **Sample #:** 4501 **Placement Date:** 07/02/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 82
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Footing **Location Details:** Headwall footing for Box culvert, STA 11+52.29. **Lat/Long:** 38.9464358 / -104.6082741

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
26	993 160059	10.00	Slump: 3 1/4 Spec: 3 - 5	Result: 6.8 Spec.: 5 - 8	138.4	85	82

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
26 / 15138	7	07/09/2025	4080	Type 3
26 / 15139	28	07/30/2025	5000	Type 2
26 / 15140	28	07/30/2025	4840	Type 2
26 / 15141	28	07/30/2025	5080	Type 2

Average Strength (psi): 7 Day - 4080 psi, 28 Day - 4970 psi

08/05/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 27 **Sample #:** 4552 **Placement Date:** 07/09/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 90
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Foundation Wall **Location Details:** Headwall east end at intersection Owl/Meridian

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
27	20-00328 160976	7.75	Slump: 3 Spec: 3 - 5	Result: 6 Spec.: 5 - 8	138.1	80	90

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
27 / 15307	7	07/16/2025	3390	Type 3
27 / 15308	28	08/06/2025	4280	Type 2
27 / 15309	56	09/03/2025	5000	Type 2
27 / 15310	56	09/03/2025	5130	Type 5

Average Strength (psi): 7 Day - 3390 psi, 28 Day - 4280 psi, 56 Day - 5060 psi

09/11/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 1 **Sample #:** 3140 **Placement Date:** 12/16/2024 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 34
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert box at south end **Lat/Long:** 38.9446233 / -104.6091133

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
1	20-00317 136629	10.00	Slump: 4 Spec: 3 - 5	Result: 6.5 Spec.: 5 - 8	137.0	71	34

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
1 / 10893	7	12/23/2024	4780	Type 2

12/30/2024

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 1 **Sample #:** 3140 **Placement Date:** 12/16/2024 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 34
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert box at south end **Lat/Long:** 38.9446233 / -104.6091133

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
1	20-00317 136629	10.00	Slump: 4 Spec: 3 - 5	Result: 6.5 Spec.: 5 - 8	137.0	71	34

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
1 / 10893	7	12/23/2024	4780	Type 2
1 / 10894	28	01/13/2025	6340	Type 3
1 / 10895	28	01/13/2025	6170	Type 5
1 / 10896	28	01/13/2025	6200	Type 3

Average Strength (psi): 7 Day - 4780 psi, 28 Day - 6240 psi

01/13/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Grout Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 1 **Sample #:** 4854 **Placement Date:** 08/11/2025 **Technician:** Hooker, Kirby

Weather Conditions: Sunny **Air Temp (°F):** 65

Grout Source: Offsite Supplier

Grout Mix Design: 40940

Specified Strength (psi): 4000

Grout Location Details:

Lat/Long: 38.9464278 / -104.6082648

Rip rap channel at north end of box culvert near the Northwest corner of Meridian Road and Owl Pl.

PLACEMENT DATA

Set #	Slump (in)	Grout Temp (°F)
1	Slump: 3 Spec: 3 - 7	82.0

"NT" = Not Tested

STRENGTH DATA

Set / Test	Age (Days)	Test Date	Strength (psi)	Remarks	Fracture Pattern
1 / 20799	7	08/18/2025	3610		Type 2
1 / 20800	28	09/08/2025	4970		Type 3
1 / 20801	28	09/08/2025	4520		Type 5
1 / 20802	28	09/08/2025	4540		Type 3

Average Strength (psi): 7 Day - 3610 psi, 28 Day - 4670 psi

01/19/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 2 **Sample #:** 3234 **Placement Date:** 01/02/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 41
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert footing, 90' N from south end **Lat/Long:** 38.9440067 / -104.6075046

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
2	20-00317 138144	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	136.8	80	41

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
2 / 11178	7	01/09/2025	4460	Type 2

01/09/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 2 **Sample #:** 3234 **Placement Date:** 01/02/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 41
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert footing, 90' N from south end **Lat/Long:** 38.9440067 / -104.6075046

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
2	20-00317 138144	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	136.8	80	41

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
2 / 11178	7	01/09/2025	4460	Type 2
2 / 11179	28	01/30/2025	5410	Type 2
2 / 11180	28	01/30/2025	5350	Type 2
2 / 11181	28	01/30/2025	5590	Type 3

Average Strength (psi): 7 Day - 4460 psi, 28 Day - 5450 psi

01/31/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 3 **Sample #:** 3237 **Placement Date:** 01/02/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 43
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert footing, 30' from North end

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
3	20-00317 138180	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 5.5 Spec.: 5 - 8	138.7	80	43

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
3 / 11190	7	01/09/2025	4580	Type 5

01/09/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 3 **Sample #:** 3237 **Placement Date:** 01/02/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 43
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert footing, 30' from North end

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
3	20-00317 138180	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 5.5 Spec.: 5 - 8	138.7	80	43

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
3 / 11190	7	01/09/2025	4580	Type 5
3 / 11191	28	01/30/2025	5760	Type 3
3 / 11192	28	01/30/2025	5970	Type 3
3 / 11193	28	01/30/2025	5900	Type 5

Average Strength (psi): 7 Day - 4580 psi, 28 Day - 5880 psi

01/31/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 4 **Sample #:** 3321 **Placement Date:** 01/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 44

Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Bridge - Wing Wall **Location Details:** Bridge Foundation wall, 60' South from North end

Notes: Additional trucks tested by Pete Lein QC

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
4	20-00325 139538	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 6.5 Spec.: 5 - 8	140.6	65	44

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
4 / 11403	7	01/31/2025	5710	Type 2

01/31/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 4 **Sample #:** 3321 **Placement Date:** 01/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 44
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Bridge - Wing Wall **Location Details:** Bridge Foundation wall, 60' South from North end

Notes: Additional trucks tested by Pete Lein QC

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
4	20-00325 139538	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 6.5 Spec.: 5 - 8	140.6	65	44

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
4 / 11403	7	01/31/2025	5710	Type 2
4 / 11404	28	02/21/2025	6900	Type 2
4 / 11405	28	02/21/2025	6700	Type 3
4 / 11406	28	02/21/2025	6700	Type 3

Average Strength (psi): 7 Day - 5710 psi, 28 Day - 6770 psi

02/21/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 5 **Sample #:** 3354 **Placement Date:** 01/31/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 46

Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Building Exterior - Foundation Wall **Location Details:** Culvert East side foundation wall center mass, 150' North from South end

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
5	20-00325 140220	10.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	136.4	74	46

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
5 / 11480	7	02/07/2025	3940	Type 2

02/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 5 **Sample #:** 3354 **Placement Date:** 01/31/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 46

Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Building Exterior - Foundation Wall **Location Details:** Culvert East side foundation wall center mass, 150' North from South end

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
5	20-00325 140220	10.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	136.4	74	46

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
5 / 11480	7	02/07/2025	3940	Type 2
5 / 11481	28	02/28/2025	5100	Type 5
5 / 11482	28	02/28/2025	5220	Type 5
5 / 11483	28	02/28/2025	5380	Type 5

Average Strength (psi): 7 Day - 3940 psi, 28 Day - 5230 psi

03/05/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 6 **Sample #:** 3392 **Placement Date:** 02/07/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 59
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Bridge - Wing Wall Footer **Location Details:** Culvert east wall, 50' North from South end **Lat/Long:** 38.9448515 / -104.6096189

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
6	20-00327 140957	10.00	Slump: 4 Spec: 3 - 5	Result: 6.5 Spec.: 5 - 8	139.6	75	59

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
6 / 11645	7	02/14/2025	4490	Type 3

02/18/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 6 **Sample #:** 3392 **Placement Date:** 02/07/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 59
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Bridge - Wing Wall Footer **Location Details:** Culvert east wall, 50' North from South end **Lat/Long:** 38.9448515 / -104.6096189

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
6	20-00327 140957	10.00	Slump: 4 Spec: 3 - 5	Result: 6.5 Spec.: 5 - 8	139.6	75	59

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
6 / 11645	7	02/14/2025	4490	Type 3
6 / 11646	28	03/07/2025	5590	Type 3
6 / 11647	28	03/07/2025	5350	Type 5
6 / 11648	28	03/07/2025	5760	Type 2

Average Strength (psi): 7 Day - 4490 psi, 28 Day - 5570 psi

03/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 7 **Sample #:** 3454 **Placement Date:** 02/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 56
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top, North end structure **Lat/Long:** 38.9456356 / -104.6094538

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
7	20-00305 141578	10.00	Slump: 3 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	137.1	72	56

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
7 / 11846	7	03/03/2025	4320	Type 2
7 / 11850	3	02/27/2025	3510	Type 3

Average Strength (psi): 7 Day - 4330 psi, 3 Day - 3510 psi

03/05/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 7 **Sample #:** 3454 **Placement Date:** 02/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 56
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top, North end structure **Lat/Long:** 38.9456356 / -104.6094538

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
7	20-00305 141578	10.00	Slump: 3 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	137.1	72	56

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
7 / 11850	3	02/27/2025	3510	Type 3
7 / 11846	7	03/03/2025	4320	Type 2
7 / 11847	28	03/24/2025	5620	Type 2
7 / 11848	28	03/24/2025	5410	Type 2
7 / 11849	28	03/24/2025	5540	Type 2

Average Strength (psi): 3 Day - 3510 psi, 7 Day - 4330 psi, 28 Day - 5520 psi

03/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 8 **Sample #:** 3457 **Placement Date:** 02/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 60
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top 60' from South end **Lat/Long:** 38.9453151 / -104.6092548

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
8	20-02248 141616	10.00	Slump: 5 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	137.1	69	60

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
8 / 11852	7	03/03/2025	3950	Type 3
8 / 11856	3	02/27/2025	3140	Type 3

Average Strength (psi): 7 Day - 3950 psi, 3 Day - 3140 psi

03/05/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 8 **Sample #:** 3457 **Placement Date:** 02/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 60
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top 60' from South end **Lat/Long:** 38.9453151 / -104.6092548

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
8	20-02248 141616	10.00	Slump: 5 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	137.1	69	60

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
8 / 11856	3	02/27/2025	3140	Type 3
8 / 11852	7	03/03/2025	3950	Type 3
8 / 11853	28	03/24/2025	5000	Type 3
8 / 11854	28	03/24/2025	4810	Type 2
8 / 11855	28	03/24/2025	5010	Type 2

Average Strength (psi): 3 Day - 3140 psi, 7 Day - 3950 psi, 28 Day - 4940 psi

03/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 9 **Sample #:** 3510 **Placement Date:** 02/28/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 59
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** East culvert wall, 30' from South end **Lat/Long:** 38.9445977 / -104.6092405

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
9	20-00317 142326	9.50	Slump: 4 1/2 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	135.2	75	59

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
9 / 12023	7	03/07/2025	3940	Type 5

03/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 9 **Sample #:** 3510 **Placement Date:** 02/28/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 59
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** East culvert wall, 30' from South end **Lat/Long:** 38.9445977 / -104.6092405

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
9	20-00317 142326	9.50	Slump: 4 1/2 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	135.2	75	59

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
9 / 12023	7	03/07/2025	3940	Type 5
9 / 12024	28	03/28/2025	5000	Type 3
9 / 12025	28	03/28/2025	4910	Type 3
9 / 12026	28	03/28/2025	4560	Type 2

Average Strength (psi): 7 Day - 3940 psi, 28 Day - 4820 psi

03/31/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 10 **Sample #:** 3580 **Placement Date:** 03/10/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 58
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top, 80' North from South end **Lat/Long:** 38.944837 / -104.6094741

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
10	20-00330 143098	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	137.1	69	58

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
10 / 12271	7	03/17/2025	4310	Type 3

03/18/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 10 **Sample #:** 3580 **Placement Date:** 03/10/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 58
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top, 80' North from South end **Lat/Long:** 38.944837 / -104.6094741

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
10	20-00330 143098	10.00	Slump: 3 1/2 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	137.1	69	58

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
10 / 12271	7	03/17/2025	4310	Type 3
10 / 12272	28	04/07/2025	5390	Type 5
10 / 12273	28	04/07/2025	5360	Type 2
10 / 12274	28	04/07/2025	5360	Type 3

Average Strength (psi): 7 Day - 4310 psi, 28 Day - 5370 psi

04/07/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 11 **Sample #:** 3582 **Placement Date:** 03/10/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 63
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top, 20' North from South end **Lat/Long:** 38.9448587 / -104.6092407

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
11	20-00317 143138	10.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	136.6	68	63

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
11 / 12277	7	03/17/2025	3780	Type 3

03/18/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 11 **Sample #:** 3582 **Placement Date:** 03/10/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 63
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** Culvert top, 20' North from South end **Lat/Long:** 38.9448587 / -104.6092407

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
11	20-00317 143138	10.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	136.6	68	63

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
11 / 12277	7	03/17/2025	3780	Type 3
11 / 12278	28	04/07/2025	4910	Type 2
11 / 12279	28	04/07/2025	4670	Type 3
11 / 12280	28	04/07/2025	4850	Type 3

Average Strength (psi): 7 Day - 3780 psi, 28 Day - 4810 psi

04/07/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 12 **Sample #:** 3607 **Placement Date:** 03/12/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 57
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Inlet base at south end of culvert **Lat/Long:** 38.9446975 / -104.6093471

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
12	20-00308 143561	8.75	Slump: 5 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	134.8	75	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
12 / 12380	7	03/19/2025	2920	Type 5

03/19/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 12 **Sample #:** 3607 **Placement Date:** 03/12/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 57
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Inlet base at south end of culvert **Lat/Long:** 38.9446975 / -104.6093471

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
12	20-00308 143561	8.75	Slump: 5 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	134.8	75	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
12 / 12380	7	03/19/2025	2920	Type 5
12 / 12381	28	04/09/2025	3530	Type 2

Average Strength (psi): 7 Day - 2920 psi, 28 Day - 3530 psi

56 Day Breaks will be provided when available.

04/11/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 12 **Sample #:** 3607 **Placement Date:** 03/12/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 57
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Inlet base at south end of culvert **Lat/Long:** 38.9446975 / -104.6093471

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
12	20-00308 143561	8.75	Slump: 5 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	134.8	75	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
12 / 12380	7	03/19/2025	2920	Type 5
12 / 12381	28	04/09/2025	3530	Type 2
12 / 12382	56	05/07/2025	4400	Type 5

Average Strength (psi): 7 Day - 2920 psi, 28 Day - 3530 psi, 56 Day - 4400 psi

05/12/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 12 **Sample #:** 3607 **Placement Date:** 03/12/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 57
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Inlet base at south end of culvert **Lat/Long:** 38.9446975 / -104.6093471

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
12	20-00308 143561	8.75	Slump: 5 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	134.8	75	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
12 / 12380	7	03/19/2025	2920	Type 5
12 / 12381	28	04/09/2025	3530	Type 2
12 / 12382	56	05/07/2025	4400	Type 5
12 / 12383	90	06/10/2025	4810	Type 3

Average Strength (psi): 7 Day - 2920 psi, 28 Day - 3530 psi, 56 Day - 4400 psi, 90 Day - 4810 psi

06/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 13 **Sample #:** 3695 **Placement Date:** 03/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 63
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Bridge - Wing Wall **Location Details:** Wing wall at the southern end of the culvert inlet **Lat/Long:** 38.9440825 / -104.6095857

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
13	20-00325 144669	8.50	Slump: 4 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	135.8	73	63

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
13 / 12666	7	03/31/2025	4130	Type 2

03/31/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 13 **Sample #:** 3695 **Placement Date:** 03/24/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 63
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Bridge - Wing Wall **Location Details:** Wing wall at the southern end of the culvert inlet **Lat/Long:** 38.9440825 / -104.6095857

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
13	20-00325 144669	8.50	Slump: 4 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	135.8	73	63

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
13 / 12666	7	03/31/2025	4130	Type 2
13 / 12667	28	04/21/2025	4910	Type 2
13 / 12668	28	04/21/2025	4920	Type 2
13 / 12669	28	04/21/2025	4820	Type 2

Average Strength (psi): 7 Day - 4130 psi, 28 Day - 4880 psi

04/28/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 14 **Sample #:** 3774 **Placement Date:** 03/31/2025 **Technician:** Michael Crytser **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 49

Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Other **Location Details:** Box culvert forebay walls at the south west corner of the site. **Lat/Long:** 38.9446589 / -104.6093474

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
14	20-00316 145651	8.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	138.0	65	49

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
14 / 12949	7	04/07/2025	4830	Type 2

04/16/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 15 **Sample #:** 4023 **Placement Date:** 04/28/2025 **Technician:** Nathan Weaver **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 57
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** At Station 0 + 35 of the Falcon Marketplace Roundabout. **Lat/Long:** 38.9440169 / -104.6112748

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
15	21-02277 149144	10.00	Slump: 4 1/4 Spec: 3 - 5	Result: 5.5 Spec.: 5 - 8	140.0	66	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
15 / 13735	7	05/05/2025	4190	Type 3

05/08/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 15 **Sample #:** 4023 **Placement Date:** 04/28/2025 **Technician:** Nathan Weaver **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 57
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Other **Location Details:** At Station 0 + 35 of the Falcon Marketplace Roundabout. **Lat/Long:** 38.9440169 / -104.6112748

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
15	21-02277 149144	10.00	Slump: 4 1/4 Spec: 3 - 5	Result: 5.5 Spec.: 5 - 8	140.0	66	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
15 / 13735	7	05/05/2025	4190	Type 3
15 / 13736	28	05/26/2025	4840	Type 3
15 / 13737	28	05/26/2025	4530	Type 2
15 / 13738	28	05/26/2025	5230	Type 3

Average Strength (psi): 7 Day - 4190 psi, 28 Day - 4870 psi

06/02/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 16 **Sample #:** 4075 **Placement Date:** 05/08/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 48
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Slab on Grade **Location Details:** At Station 10 + 00. **Lat/Long:** 38.9463513 / -104.6093292

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
16	20-00331 150498	10.00	Slump: 5 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	138.0	77	48

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
16 / 13930	7	05/15/2025	3960	Type 2

05/25/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 16 **Sample #:** 4075 **Placement Date:** 05/08/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 48
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Slab on Grade **Location Details:** At Station 10 + 00. **Lat/Long:** 38.9463513 / -104.6093292

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
16	20-00331 150498	10.00	Slump: 5 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	138.0	77	48

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
16 / 13930	7	05/15/2025	3960	Type 2
16 / 13931	28	06/05/2025	5120	Type 2
16 / 13932	28	06/05/2025	5540	Type 2
16 / 13933	28	06/05/2025	5140	Type 2

Average Strength (psi): 7 Day - 3960 psi, 28 Day - 5270 psi

06/07/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 17 **Sample #:** 4078 **Placement Date:** 05/08/2025 **Technician:** Kirby Hooker **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 51
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Interior - Slab on Grade **Location Details:** At Station 7+50. **Lat/Long:** 38.9463316 / -104.6093101

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
17	20-00305 150534	10.00	Slump: 5 Spec: 3 - 5	Result: 6.6 Spec.: 5 - 8	139.2	78	51

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
17 / 13938	7	05/15/2025	4190	Type 3

05/25/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 17 **Sample #: 4078** **Placement Date:** 05/08/2025 **Technician:** Kirby Hooker **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 51
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Interior - Slab on Grade **Location Details:** At Station 7+50. **Lat/Long:** 38.9463316 / -104.6093101

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
17	20-00305 150534	10.00	Slump: 5 Spec: 3 - 5	Result: 6.6 Spec.: 5 - 8	139.2	78	51

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
17 / 13938	7	05/15/2025	4190	Type 3
17 / 13939	28	06/05/2025	5660	Type 2
17 / 13940	28	06/05/2025	5790	Type 2
17 / 13941	28	06/05/2025	5820	Type 3

Average Strength (psi): 7 Day - 4190 psi, 28 Day - 5760 psi

06/07/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 18 **Sample #:** 4166 **Placement Date:** 05/20/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 54
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** At the northwest corner of the culvert. **Lat/Long:** 38.9462047 / -104.6092239

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
18	995 152596	10.00	Slump: 4 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	136.8	74	54

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
18 / 14205	7	05/27/2025	4100	Type 3

06/11/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 18 **Sample #:** 4166 **Placement Date:** 05/20/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 54
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** At the northwest corner of the culvert. **Lat/Long:** 38.9462047 / -104.6092239

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
18	995 152596	10.00	Slump: 4 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	136.8	74	54

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
18 / 14205	7	05/27/2025	4100	Type 3
18 / 14206	28	06/17/2025	4670	Type 2
18 / 14207	28	06/17/2025	4820	Type 2
18 / 14208	28	06/17/2025	4630	Type 2

Average Strength (psi): 7 Day - 4100 psi, 28 Day - 4710 psi

06/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 19 **Sample #:** 4173 **Placement Date:** 05/20/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 59

Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Inlet Box **Location Details:** From the northeast corner of of Falcon Market Place and Owl Place, 10 feet east and 20 feet south. **Lat/Long:** 38.9463463 / -104.6085667

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
19	20-00311 152651	10.00	Slump: 5 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	139.2	68	59

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
19 / 14217	7	05/27/2025	3990	Type 2

06/11/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 19 **Sample #:** 4173 **Placement Date:** 05/20/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 59

Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500

Placement Location: Inlet Box **Location Details:** From the northeast corner of of Falcon Market Place and Owl Place, 10 feet east and 20 feet south. **Lat/Long:** 38.9463463 / -104.6085667

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
19	20-00311 152651	10.00	Slump: 5 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	139.2	68	59

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
19 / 14217	7	05/27/2025	3990	Type 2
19 / 14218	28	06/17/2025	5660	Type 2
19 / 14219	28	06/17/2025	5390	Type 2
19 / 14220	28	06/17/2025	5440	Type 2

Average Strength (psi): 7 Day - 3990 psi, 28 Day - 5490 psi

06/24/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 20 **Sample #:** 4259 **Placement Date:** 05/30/2025 **Technician:** Herbert Hafenrichter **Weather Conditions:** Sunny **Air Temp (°F):** 61
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** Culvert at the northwest corner of the project. **Lat/Long:** 38.94824173 / -104.60815031

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
20	21-02276 154326	10.00	Slump: 4 Spec: 3 - 5	Result: 7.9 Spec.: 5 - 8	138.0	65	61

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
20 / 14582	7	06/06/2025	3580	Type 3
20 / 14583	28	06/27/2025	5210	Type 3
20 / 14584	28	06/27/2025	4770	Type 2
20 / 14585	28	06/27/2025	4940	Type 2

Average Strength (psi): 7 Day - 3580 psi, 28 Day - 4980 psi

07/07/2025

Reviewed by: Robert Jaquet, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 21 **Sample #:** 4268 **Placement Date:** 05/30/2025 **Technician:** Herbert Hafenrichter **Weather Conditions:** Sunny **Air Temp (°F):** 68
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** From the northwest corner of the site, 30 feet east.

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
21	988 154407	10.00	Slump: 4 Spec: 3 - 5	Result: 7 Spec.: 5 - 8	140.8	70	68

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
21 / 14586	7	06/06/2025	3750	Type 3
21 / 14587	28	06/27/2025	5410	Type 2
21 / 14588	28	06/27/2025	5170	Type 5
21 / 14589	28	06/27/2025	5190	Type 5

Average Strength (psi): 7 Day - 3750 psi, 28 Day - 5260 psi

07/07/2025

Reviewed by: Robert Jaquet, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 22 **Sample #:** 4309 **Placement Date:** 06/09/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 70
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Culvert top, north branch 80' from Meridian Road. **Lat/Long:** 38.9458696 / -104.608054

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
22	21-02295 155816	10.00	Slump: 4 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	138.3	75	70

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
22 / 14620	7	06/16/2025	3820	Type 2

07/07/2025

Reviewed by: Robert Jaquet, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 22 **Sample #:** 4309 **Placement Date:** 06/09/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 70
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Culvert top, north branch 80' from Meridian Road. **Lat/Long:** 38.9458696 / -104.608054

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
22	21-02295 155816	10.00	Slump: 4 Spec: 3 - 5	Result: 8 Spec.: 5 - 8	138.3	75	70

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
22 / 14620	7	06/16/2025	3820	Type 2
22 / 14621	28	07/07/2025	4740	Type 2
22 / 14622	28	07/07/2025	4870	Type 2
22 / 14623	28	07/07/2025	4860	Type 3

Average Strength (psi): 7 Day - 3820 psi, 28 Day - 4820 psi

07/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 23 **Sample #:** 4332 **Placement Date:** 06/11/2025 **Technician:** Michael Crytser **Weather Conditions:** Sunny **Air Temp (°F):** 80
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** North most Culvert Pad. **Lat/Long:** 38.9465516 / -104.6084235

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
23	21-02272 156397	10.00	Slump: 4 Spec: 3 - 5	Result: 7.8 Spec.: 5 - 8	138.0	85	80

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
23 / 14690	7	06/18/2025	3580	Type 2

07/07/2025

Reviewed by: Robert Jaquet, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 23 **Sample #:** 4332 **Placement Date:** 06/11/2025 **Technician:** Michael Crytser **Weather Conditions:** Sunny **Air Temp (°F):** 80
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** North most Culvert Pad. **Lat/Long:** 38.9465516 / -104.6084235

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
23	21-02272 156397	10.00	Slump: 4 Spec: 3 - 5	Result: 7.8 Spec.: 5 - 8	138.0	85	80

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
23 / 14690	7	06/18/2025	3580	Type 2
23 / 14691	28	07/09/2025	4570	Type 2
23 / 14692	28	07/09/2025	4570	Type 2
23 / 14693	28	07/09/2025	4480	Type 3

Average Strength (psi): 7 Day - 3580 psi, 28 Day - 4540 psi

07/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 24 **Sample #:** 4379 **Placement Date:** 06/18/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 66
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Box Culvert at Station 10+50.

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
24	20-00332 157626	9.00	Slump: 4 Spec: 3 - 5	Result: 7.8 Spec.: 5 - 8	137.2	80	66

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
24 / 14827	8	06/25/2025	3370	Type 2

07/07/2025

Reviewed by: Robert Jaquet, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 24 **Sample #:** 4379 **Placement Date:** 06/18/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 66
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Box Culvert at Station 10+50.

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
24	20-00332 157626	9.00	Slump: 4 Spec: 3 - 5	Result: 7.8 Spec.: 5 - 8	137.2	80	66

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
24 / 14827	8	06/25/2025	3370	Type 2
24 / 14828	28	07/16/2025	3950	Type 3

Average Strength (psi): 8 Day - 3370 psi, 28 Day - 3950 psi

56 Day Breaks will be provided when available.

07/23/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 24 **Sample #:** 4379 **Placement Date:** 06/18/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 66
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Inlet Box **Location Details:** Box Culvert at Station 10+50.

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
24	20-00332 157626	9.00	Slump: 4 Spec: 3 - 5	Result: 7.8 Spec.: 5 - 8	137.2	80	66

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
24 / 14827	8	06/25/2025	3370	Type 2
24 / 14828	28	07/16/2025	3950	Type 3
24 / 14829	56	08/13/2025	5090	Type 5
24 / 14830	56	08/13/2025	5110	Type 3

Average Strength (psi): 8 Day - 3370 psi, 28 Day - 3950 psi, 56 Day - 5100 psi

08/18/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 25 **Sample #:** 4444 **Placement Date:** 06/25/2025 **Technician:** Herbert Hafenrichter **Weather Conditions:** Sunny / Cloudy **Air Temp (°F):** 73
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** From the Northeast corner of the culvert pad. **Lat/Long:** 38.94514973 / -104.60862881

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
25	20-00329 158844	9.25	Slump: 3 Spec: 3 - 5	Result: 6.8 Spec.: 5 - 8	139.2	75	73

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
25 / 14982	7	07/02/2025	3810	Type 5

07/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 25 **Sample #:** 4444 **Placement Date:** 06/25/2025 **Technician:** Herbert Hafenrichter **Weather Conditions:** Sunny / Cloudy **Air Temp (°F):** 73
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Other **Location Details:** From the Northeast corner of the culvert pad. **Lat/Long:** 38.94514973 / -104.60862881

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
25	20-00329 158844	9.25	Slump: 3 Spec: 3 - 5	Result: 6.8 Spec.: 5 - 8	139.2	75	73

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
25 / 14982	7	07/02/2025	3810	Type 5
25 / 14983	28	07/23/2025	5100	Type 3
25 / 14984	28	07/23/2025	5230	Type 2
25 / 14985	28	07/23/2025	5250	Type 3

Average Strength (psi): 7 Day - 3810 psi, 28 Day - 5190 psi

07/25/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 26 **Sample #:** 4501 **Placement Date:** 07/02/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 82
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Footing **Location Details:** Headwall footing for Box culvert, STA 11+52.29. **Lat/Long:** 38.9464358 / -104.6082741

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
26	993 160059	10.00	Slump: 3 1/4 Spec: 3 - 5	Result: 6.8 Spec.: 5 - 8	138.4	85	82

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
26 / 15138	7	07/09/2025	4080	Type 3

07/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 26 **Sample #:** 4501 **Placement Date:** 07/02/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 82
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Footing **Location Details:** Headwall footing for Box culvert, STA 11+52.29. **Lat/Long:** 38.9464358 / -104.6082741

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
26	993 160059	10.00	Slump: 3 1/4 Spec: 3 - 5	Result: 6.8 Spec.: 5 - 8	138.4	85	82

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
26 / 15138	7	07/09/2025	4080	Type 3
26 / 15139	28	07/30/2025	5000	Type 2
26 / 15140	28	07/30/2025	4840	Type 2
26 / 15141	28	07/30/2025	5080	Type 2

Average Strength (psi): 7 Day - 4080 psi, 28 Day - 4970 psi

08/05/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 27 **Sample #:** 4552 **Placement Date:** 07/09/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 90
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Foundation Wall **Location Details:** Headwall east end at intersection Owl/Meridian

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
27	20-00328 160976	7.75	Slump: 3 Spec: 3 - 5	Result: 6 Spec.: 5 - 8	138.1	80	90

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
27 / 15307	7	07/16/2025	3390	Type 3

07/23/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 27 **Sample #:** 4552 **Placement Date:** 07/09/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 90
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Foundation Wall **Location Details:** Headwall east end at intersection Owl/Meridian

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
27	20-00328 160976	7.75	Slump: 3 Spec: 3 - 5	Result: 6 Spec.: 5 - 8	138.1	80	90

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
27 / 15307	7	07/16/2025	3390	Type 3
27 / 15308	28	08/06/2025	4280	Type 2

Average Strength (psi): 7 Day - 3390 psi, 28 Day - 4280 psi

56 Day Breaks will be provided when available.

08/18/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 27 **Sample #:** 4552 **Placement Date:** 07/09/2025 **Technician:** Jayce Barnhart **Weather Conditions:** Sunny **Air Temp (°F):** 90
Contractor: PPC Construction **Supplier:** Pete Lien **Mix Design:** 90DJ50 **Specified Strength (psi):** 4500
Placement Location: Building Exterior - Foundation Wall **Location Details:** Headwall east end at intersection Owl/Meridian

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
27	20-00328 160976	7.75	Slump: 3 Spec: 3 - 5	Result: 6 Spec.: 5 - 8	138.1	80	90

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
27 / 15307	7	07/16/2025	3390	Type 3
27 / 15308	28	08/06/2025	4280	Type 2
27 / 15309	56	09/03/2025	5000	Type 2
27 / 15310	56	09/03/2025	5130	Type 5

Average Strength (psi): 7 Day - 3390 psi, 28 Day - 4280 psi, 56 Day - 5060 psi

09/11/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 28 **Sample #:** 5786 **Placement Date:** 10/27/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny / Partly Cloudy **Air Temp (°F):** 66
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34682110 **Specified Strength (psi):** 4500
Placement Location: Curb & Gutter **Location Details:** At Station 8+00 along Meridian Park Drive. **Lat/Long:** 38.9457484 / -104.6089086

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
28	350 71406278	11.00	Slump: 1 Spec: 1/2 - 2 1/2	Result: 6 Spec.: 5 - 8	140.4	82	66

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
28 / 18942	7	11/03/2025	3730	Type 3

Average Strength (psi): 7 Day - 3740 psi

11/18/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 28 **Sample #:** 5786 **Placement Date:** 10/27/2025 **Technician:** Hooker, Kirby **Weather Conditions:** Sunny / Partly Cloudy **Air Temp (°F):** 66
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34682110 **Specified Strength (psi):** 4500
Placement Location: Curb & Gutter **Location Details:** At Station 8+00 along Meridian Park Drive. **Lat/Long:** 38.9457484 / -104.6089086

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
28	350 71406278	11.00	Slump: 1 Spec: 1/2 - 2 1/2	Result: 6 Spec.: 5 - 8	140.4	82	66

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
28 / 18942	7	11/03/2025	3730	Type 3
28 / 18943	28	11/24/2025	5360	Type 2
28 / 18944	28	11/24/2025	4980	Type 2
28 / 18945	28	11/24/2025	4940	Type 2

Average Strength (psi): 7 Day - 3740 psi, 28 Day - 5090 psi

11/28/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 29 **Sample #:** 5787 **Placement Date:** 10/27/2025 **Technician:** Kirby Hooker **Weather Conditions:** Sunny / Partly Cloudy **Air Temp (°F):** 66
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34682110 **Specified Strength (psi):** 4500
Placement Location: Curb & Gutter **Location Details:** At Station 5+75 along Meridian Park Drive. **Lat/Long:** 38.9454944 / -104.6091058

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
29	59 71406290	12.00	Slump: 1 Spec: 1/2 - 2 1/2	Result: 5.5 Spec.: 5 - 8	141.2	80	66

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
29 / 18946	7	11/03/2025	4180	Type 3

Average Strength (psi): 7 Day - 4180 psi

11/18/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 29 **Sample #:** 5787 **Placement Date:** 10/27/2025 **Technician:** Hooker, Kirby **Weather Conditions:** Sunny / Partly Cloudy **Air Temp (°F):** 66
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34682110 **Specified Strength (psi):** 4500
Placement Location: Curb & Gutter **Location Details:** At Station 5+75 along Meridian Park Drive. **Lat/Long:** 38.9454944 / -104.6091058

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
29	59 71406290	12.00	Slump: 1 Spec: 1/2 - 2 1/2	Result: 5.5 Spec.: 5 - 8	141.2	80	66

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
29 / 18946	7	11/03/2025	4180	Type 3
29 / 18947	28	11/24/2025	5200	Type 2
29 / 18948	28	11/24/2025	5300	Type 3
29 / 18949	28	11/24/2025	4990	Type 2

Average Strength (psi): 7 Day - 4180 psi, 28 Day - 5170 psi

11/28/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 30 **Sample #:** 6167 **Placement Date:** 11/21/2025 **Technician:** Barnhart, Jayce **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 42
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Crosspan **Location Details:** Cross pan from owl marketplace onto street 200' North from roundabout **Lat/Long:** 38.9456361 / -104.6091546

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
30	43 71407360	10.00	Slump: 4 Spec: 3 - 5	Result: 5.5 Spec.: 5 - 8	135.9	70	42

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
30 / 20090	7	11/28/2025	4290	Type 2

Average Strength (psi): 7 Day - 4290 psi

12/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 30 **Sample #:** 6167 **Placement Date:** 11/21/2025 **Technician:** Barnhart, Jayce **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 42

Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Crosspan **Location Details:** Cross pan from owl marketplace onto street 200' North from roundabout **Lat/Long:** 38.9456361 / -104.6091546

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
30	43 71407360	10.00	Slump: 4 Spec: 3 - 5	Result: 5.5 Spec.: 5 - 8	135.9	70	42

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
30 / 20090	7	11/28/2025	4290	Type 2
30 / 20091	28	12/19/2025	4980	Type 2
30 / 20092	28	12/19/2025	4760	Type 2
30 / 20093	28	12/19/2025	5090	Type 2

Average Strength (psi): 7 Day - 4290 psi, 28 Day - 4950 psi

12/30/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 31 **Sample #:** 6210 **Placement Date:** 11/26/2025 **Technician:** Oswald, Andrew **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 28
Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Crosspan **Location Details:** Cross pan, STA 5+25 on Meridian Park Dr. **Lat/Long:** 38.9449167 / -104.6090249

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
31	7 71407476	10.00	Slump: 4 1/4 Spec: 2 - 6	Result: 5.6 Spec.: 5 - 8	137.2	76	28

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
31 / 20225	7	12/03/2025	3550	Type 5

Average Strength (psi): 7 Day - 3550 psi

12/10/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 31 **Sample #:** 6210 **Placement Date:** 11/26/2025 **Technician:** Oswald, Andrew **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 28
Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Crosspan **Location Details:** Cross pan, STA 5+25 on Meridian Park Dr. **Lat/Long:** 38.9449167 / -104.6090249

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
31	7 71407476	10.00	Slump: 4 1/4 Spec: 2 - 6	Result: 5.6 Spec.: 5 - 8	137.2	76	28

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
31 / 20225	7	12/03/2025	3550	Type 5
31 / 20226	28	12/24/2025	4700	Type 5
31 / 20227	28	12/24/2025	4540	Type 5
31 / 20228	28	12/24/2025	5110	Type 2

Average Strength (psi): 7 Day - 3550 psi, 28 Day - 4780 psi

12/30/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 32 **Sample #:** 6261 **Placement Date:** 12/06/2025 **Technician:** Crytser, Michael **Weather Conditions:** Sunny **Air Temp (°F):** 42
Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Curb & Gutter **Location Details:** Median starting at the south west point going north. South west corner of site **Lat/Long:** 38.9445305 / -104.6087511

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
32	68 71407670	12.00	Slump: 3 3/4 Spec: 3 - 5	Result: 5.8 Spec.: 5 - 8	138.8	70	42

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
32 / 20435	7	12/13/2025	4020	Type 2

Average Strength (psi): 9 Day - 4020 psi

12/19/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 32 **Sample #:** 6261 **Placement Date:** 12/06/2025 **Technician:** Michael, Crytser **Weather Conditions:** Sunny **Air Temp (°F):** 42
Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Curb & Gutter **Location Details:** Meridian Park Dr. Sta 3+00 starting at the south west point going north. South west corner of site **Lat/Long:** 38.9445305 / -104.6087511

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
32	68 71407670	12.00	Slump: 3 3/4 Spec: 3 - 5	Result: 5.8 Spec.: 5 - 8	138.8	70	42

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
32 / 20435	7	12/13/2025	4020	Type 2
32 / 20436	28	01/03/2026	4560	Type 2
32 / 20437	28	01/03/2026	4830	Type 2
32 / 20438	28	01/03/2026	4920	Type 2

Average Strength (psi): 7 Day - 4020 psi, 28 Day - 4770 psi

01/19/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 33 **Sample #:** 6281 **Placement Date:** 12/09/2025 **Technician:** Hooker, Kirby **Weather Conditions:** Cloudy **Air Temp (°F):** 43
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Curb & Gutter **Location Details:** STA 3 + 25 on East side of Meridian Park Dr. and STA 1 + 00 thru STA 2 + 50 on West side of Meridian Park Dr. **Lat/Long:** 38.944747 / -104.6088432

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
33	7 71407714	10.00	Slump: 4 Spec: 2 - 6	Result: 5 Spec.: 5 - 8	140.4	70	43

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
33 / 20399	7	12/16/2025	4610	Type 3

Average Strength (psi): 7 Day - 4610 psi

12/19/2025

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 33 **Sample #:** 6281 **Placement Date:** 12/09/2025 **Technician:** Kirby, Hooker **Weather Conditions:** Cloudy **Air Temp (°F):** 43

Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Curb & Gutter **Location Details:** STA 3 + 25 on East side of Meridian Park Dr. and STA 1 + 00 thru STA 2 + 50 on West side of Meridian Park Dr. **Lat/Long:** 38.944747 / -104.6088432

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
33	7 71407714	10.00	Slump: 4 Spec: 2 - 6	Result: 5 Spec.: 5 - 8	140.4	70	43

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
33 / 20399	7	12/16/2025	4610	Type 3
33 / 20400	28	01/06/2026	5870	Type 2
33 / 20401	28	01/06/2026	5400	Type 2
33 / 20402	28	01/06/2026	5730	Type 3

Average Strength (psi): 7 Day - 4610 psi, 28 Day - 5670 psi

01/19/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 34 **Sample #:** 6971 **Placement Date:** 02/18/2026 **Technician:** Michael Crytser **Weather Conditions:** Sunny / Windy **Air Temp (°F):** 37

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34682110 **Specified Strength (psi):** 4500

Placement Location: Curb & Gutter **Location Details:** Curb and Gutter on the Southbound lane of Owl Pl.,
20' west of the Southwest corner of Owl Pl. and Meridian Rd. **Lat/Long:** 38.9460355 / -104.6081509

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
34	81 71409780	10.00	Slump: 2 Spec: - 3	Result: 6.5 Spec.: 5 - 8	140.4	65	37

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
34 / 22846	7	02/25/2026	4700	Type 3

Average Strength (psi): 7 Day - 4700 psi

02/25/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 34 **Sample #:** 6971 **Placement Date:** 02/18/2026 **Technician:** Michael Crytser **Weather Conditions:** Sunny / Windy **Air Temp (°F):** 37

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34682110 **Specified Strength (psi):** 4500

Placement Location: Curb & Gutter **Location Details:** Curb and Gutter on the Southbound lane of Owl Pl.,
20' west of the Southwest corner of Owl Pl. and Meridian Rd. **Lat/Long:** 38.9460355 / -104.6081509

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
34	81 71409780	10.00	Slump: 2 Spec: - 3	Result: 6.5 Spec.: 5 - 8	140.4	65	37

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
34 / 22846	7	02/25/2026	4700	Type 3
34 / 22847	28	03/18/2026	5780	Type 2
34 / 22854	28	03/18/2026	5800	Type 2
34 / 22855	28	03/18/2026	5800	Type 2

Average Strength (psi): 7 Day - 4700 psi, 28 Day - 5790 psi

03/19/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 35 **Sample #:** 7035 **Placement Date:** 02/24/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 60
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Curb & Gutter **Location Details:** Curb and Gutter on the Northbound lane of Meridian Park Dr., at STA 9+05 **Lat/Long:** 38.9460983 / -104.6088829

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
35	5 71410052	5.00	Slump: 3 1/2 Spec: 3 - 7	Result: 7 Spec.: 5 - 8	138.0	74	60

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
35 / 23053	7	03/03/2026	4020	Type 2

Average Strength (psi): 7 Day - 4020 psi

03/09/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 35 **Sample #:** 7035 **Placement Date:** 02/24/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 60

Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Curb & Gutter **Location Details:** Curb and Gutter on the Northbound lane of Meridian Park Dr., at STA 9+05 **Lat/Long:** 38.9460983 / -104.6088829

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
35	5 71410052	5.00	Slump: 3 1/2 Spec: 3 - 7	Result: 7 Spec.: 5 - 8	138.0	74	60

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
35 / 23053	7	03/03/2026	4020	Type 2
35 / 23054	28	03/24/2026	4940	Type 2
35 / 23055	28	03/24/2026	4370	Type 2
35 / 23056	28	03/24/2026	4540	Type 2

Average Strength (psi): 7 Day - 4020 psi, 28 Day - 4610 psi

04/29/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 36 **Sample #:** 7047 **Placement Date:** 02/25/2026 **Technician:** Nathan Weaver **Weather Conditions:** Partly Cloudy / Windy **Air Temp (°F):** 57

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Curb & Gutter **Location Details:** Curb and Gutter on the Southbound lane of Meridian Rd.,
15' North of the Northwest corner of Meridian Rd. and Owl Pl. **Lat/Long:** 38.9462405 / -104.6078637

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
36	352 71410116	5.00	Slump: 4 Spec: 3 - 7	Result: 7 Spec.: 5 - 8	137.5	76	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
36 / 23073	7	03/04/2026	3680	Type 3

Average Strength (psi): 7 Day - 3680 psi

03/09/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 36 **Sample #:** 7047 **Placement Date:** 02/25/2026 **Technician:** Nathan Weaver **Weather Conditions:** Partly Cloudy / Windy **Air Temp (°F):** 57

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Curb & Gutter **Location Details:** Curb and Gutter on the Southbound lane of Meridian Rd.,
15' North of the Northwest corner of Meridian Rd. and Owl Pl. **Lat/Long:** 38.9462405 / -104.6078637

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
36	352 71410116	5.00	Slump: 4 Spec: 3 - 7	Result: 7 Spec.: 5 - 8	137.5	76	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
36 / 23073	7	03/04/2026	3680	Type 3
36 / 23074	28	03/25/2026	4310	Type 3

Average Strength (psi): 7 Day - 3680 psi, 28 Day - 4310 psi

56 Day Breaks will be provided when available.

03/29/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 36 **Sample #:** 7047 **Placement Date:** 02/25/2026 **Technician:** Nathan Weaver **Weather Conditions:** Partly Cloudy / Windy **Air Temp (°F):** 57

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Curb & Gutter **Location Details:** Curb and Gutter on the Southbound lane of Meridian Rd.,
15' North of the Northwest corner of Meridian Rd. and Owl
Pl. **Lat/Long:** 38.9462405 / -104.6078637

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
36	352 71410116	5.00	Slump: 4 Spec: 3 - 7	Result: 7 Spec.: 5 - 8	137.5	76	57

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
36 / 23073	7	03/04/2026	3680	Type 3
36 / 23074	28	03/25/2026	4310	Type 3
36 / 23075	56	04/22/2026	4590	Type 2
36 / 23076	56	04/22/2026	4720	Type 3

Average Strength (psi): 7 Day - 3680 psi, 28 Day - 4310 psi, 56 Day - 4660 psi

04/29/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 37 **Sample #:** 7248 **Placement Date:** 03/17/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 50
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T15082110 **Specified Strength (psi):** 5000
Placement Location: Curb & Gutter **Location Details:** STA 4 + 41 in the southbound lane of Meridian Rd. **Lat/Long:** 38.9461035 / -104.6076814

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
37	81 71411119	7.00	Slump: 6 Spec: 3 - 6	Result: 5.8 Spec.: 5 - 8	138.8	66	50

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
37 / 23806	7	03/24/2026	4250	Type 2

Average Strength (psi): 7 Day - 4250 psi

03/29/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 37 **Sample #:** 7248 **Placement Date:** 03/17/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 50
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T15082110 **Specified Strength (psi):** 5000
Placement Location: Curb & Gutter **Location Details:** STA 4 + 41 in the southbound lane of Meridian Rd. **Lat/Long:** 38.9461035 / -104.6076814

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
37	81 71411119	7.00	Slump: 6 Spec: 3 - 6	Result: 5.8 Spec.: 5 - 8	138.8	66	50

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
37 / 23806	7	03/24/2026	4250	Type 2
37 / 23807	28	04/14/2026	4660	Type 3

Average Strength (psi): 7 Day - 4250 psi, 28 Day - 4670 psi

56 Day Breaks will be provided when available.

04/29/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 37 **Sample #:** 7248 **Placement Date:** 03/17/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 50
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T15082110 **Specified Strength (psi):** 5000
Placement Location: Curb & Gutter **Location Details:** STA 4 + 41 in the southbound lane of Meridian Rd. **Lat/Long:** 38.9461035 / -104.6076814

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
37	81 71411119	7.00	Slump: 6 Spec: 3 - 6	Result: 5.8 Spec.: 5 - 8	138.8	66	50

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
37 / 23806	7	03/24/2026	4250	Type 2
37 / 23807	28	04/14/2026	4660	Type 3
37 / 23808	56	05/12/2026	4790	Type 2

Average Strength (psi): 7 Day - 4250 psi, 28 Day - 4670 psi, 56 Day - 4790 psi

05/19/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 37 **Sample #:** 7248 **Placement Date:** 03/17/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 50
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T15082110 **Specified Strength (psi):** 5000
Placement Location: Curb & Gutter **Location Details:** STA 4 + 41 in the southbound lane of Meridian Rd. **Lat/Long:** 38.9461035 / -104.6076814

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
37	81 71411119	7.00	Slump: 6 Spec: 3 - 6	Result: 5.8 Spec.: 5 - 8	138.8	66	50

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
37 / 23806	7	03/24/2026	4250	Type 2
37 / 23807	28	04/14/2026	4660	Type 3
37 / 23808	56	05/12/2026	4790	Type 2
37 / 23809	90	06/15/2026	5020	Type 3

Average Strength (psi): 7 Day - 4250 psi, 28 Day - 4670 psi, 56 Day - 4790 psi, 90 Day - 5020 psi

06/19/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 38 **Sample #:** 7834 **Placement Date:** 04/29/2026 **Technician:** Michael Crytser **Weather Conditions:** Cloudy **Air Temp (°F):** 39

Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Sidewalk on Meridian Dr., 40' South of the Southwest corner of Meridian Dr. and Owl Pl. **Lat/Long:** 38.9459863 / -104.6091414

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
38	346 71414003	10.00	Slump: 4 1/2 Spec: 4 - 6	Result: 5.5 Spec.: 5 - 8	138.4	70	39

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
38 / 26086	7	05/06/2026	3960	Type 5

Average Strength (psi): 7 Day - 3960 psi

05/08/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 38 **Sample #:** 7834 **Placement Date:** 04/29/2026 **Technician:** Michael Crytser **Weather Conditions:** Cloudy **Air Temp (°F):** 39
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** Sidewalk on Meridian Dr., 40' South of the Southwest corner of Meridian Dr. and Owl Pl. **Lat/Long:** 38.9459863 / -104.6091414

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
38	346 71414003	10.00	Slump: 4 1/2 Spec: 4 - 6	Result: 5.5 Spec.: 5 - 8	138.4	70	39

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
38 / 26086	7	05/06/2026	3960	Type 5
38 / 26087	28	05/27/2026	4520	Type 2
38 / 26088	28	05/27/2026	4930	Type 3
38 / 26089	28	05/27/2026	4880	Type 3

Average Strength (psi): 7 Day - 3960 psi, 28 Day - 4780 psi

06/01/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 39 **Sample #:** 7852 **Placement Date:** 05/01/2026 **Technician:** Mike Gutierrez **Weather Conditions:** Cloudy **Air Temp (°F):** 49
Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** Southbound lane of Falcon Marketplace, 300' South of Southwest corner of Falcon MP, and Owl PI **Lat/Long:** 38.9448009 / -104.6090361

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
39	7 71414051	10.00	Slump: 3 Spec: 3 - 5	Result: 5 Spec.: 5 - 8	141.3	75	49

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
39 / 26102	7	05/08/2026	3640	Type 2
39 / 26103	28	05/29/2026	4650	Type 3
39 / 26104	28	05/29/2026	4530	Type 2
39 / 26105	28	05/29/2026	4470	Type 2

Average Strength (psi): 7 Day - 3640 psi, 28 Day - 4550 psi

06/03/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 40 **Sample #:** 7864 **Placement Date:** 05/04/2026 **Technician:** Michael Crytser **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 62

Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** South end of Meridian Park Rd at roundabout entrance West side. **Lat/Long:** 38.9444949 / -104.6087673

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
40	47 71414170	10.00	Slump: 5 Spec: 4 - 6	Result: 5.6 Spec.: 5 - 8	139.2	70	62

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
40 / 26169	7	05/11/2026	3770	Type 3
40 / 26170	28	06/01/2026	5130	Type 2
40 / 26171	28	06/01/2026	4810	Type 2
40 / 26172	28	06/01/2026	5270	Type 3

Average Strength (psi): 7 Day - 3770 psi, 28 Day - 5070 psi

06/03/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 41 **Sample #:** 7884 **Placement Date:** 05/07/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 61
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** At Station 6+00 along Meridian Park Drive. **Lat/Long:** 38.9450733 / -104.6088932

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
41	61 71414275	10.00	Slump: 5 1/4 Spec: 4 - 6	Result: 5.5 Spec.: 5 - 8	139.2	68	61

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
41 / 26304	7	05/14/2026	3770	Type 3

Average Strength (psi): 7 Day - 3770 psi

05/19/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 41 **Sample #:** 7884 **Placement Date:** 05/07/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 61
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** At Station 6+00 along Meridian Park Drive. **Lat/Long:** 38.9450733 / -104.6088932

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
41	61 71414275	10.00	Slump: 5 1/4 Spec: 4 - 6	Result: 5.5 Spec.: 5 - 8	139.2	68	61

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
41 / 26304	7	05/14/2026	3770	Type 3
41 / 26305	28	06/04/2026	4960	Type 2
41 / 26306	28	06/04/2026	4750	Type 3
41 / 26307	28	06/04/2026	4700	Type 2

Average Strength (psi): 7 Day - 3770 psi, 28 Day - 4800 psi

06/05/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 42 **Sample #:** 7897 **Placement Date:** 05/08/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 50
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** Station 7+25 along Meridian Park Drive. **Lat/Long:** 38.945599 / -104.6088691

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
42	8699 71414342	10.00	Slump: 5 1/4 Spec: 4 - 6	Result: 5.2 Spec.: 5 - 8	141.2	61	50

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
42 / 26323	7	05/15/2026	3810	Type 6

Average Strength (psi): 7 Day - 3810 psi

05/19/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 42 **Sample #:** 7897 **Placement Date:** 05/08/2026 **Technician:** Rodney Fannin **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 50
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** Station 7+25 along Meridian Park Drive. **Lat/Long:** 38.945599 / -104.6088691

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
42	8699 71414342	10.00	Slump: 5 1/4 Spec: 4 - 6	Result: 5.2 Spec.: 5 - 8	141.2	61	50

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
42 / 26323	7	05/15/2026	3810	Type 6
42 / 26324	28	06/05/2026	4810	Type 3
42 / 26325	28	06/05/2026	4810	Type 5
42 / 26326	28	06/05/2026	4570	Type 5

Average Strength (psi): 7 Day - 3810 psi, 28 Day - 4730 psi

06/09/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 43 **Sample #:** 7936 **Placement Date:** 05/11/2026 **Technician:** Jonathan Decker **Weather Conditions:** Sunny **Air Temp (°F):** 70
Contractor: Pyramid **Supplier:** Amrize **Mix Design:** 74082110 (Draft) **Specified Strength (psi):** 4000

Placement Location: Other

Location Details: Median decorative covering, the north median of the roundabout on Eastonville.

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
43	85 71414504	10.00	Slump: 4 3/4 Spec: 3 - 5	Result: 7.8 Spec.: 5 - 8	135.6	75	70

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
43 / 26466	7	05/18/2026	4310	Type 3

Average Strength (psi): 7 Day - 4310 psi

06/03/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 43 **Sample #:** 7936 **Placement Date:** 05/11/2026 **Technician:** Jonathan Decker **Weather Conditions:** Sunny **Air Temp (°F):** 70
Contractor: Pyramid **Supplier:** Amrize **Mix Design:** 74082110 (Draft) **Specified Strength (psi):** 4000

Placement Location: Other

Location Details: Median decorative covering, the north median of the roundabout on Eastonville.

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
43	85 71414504	10.00	Slump: 4 3/4 Spec: 3 - 5	Result: 7.8 Spec.: 5 - 8	135.6	75	70

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
43 / 26466	7	05/18/2026	4310	Type 3
43 / 26467	28	06/08/2026	5020	Type 3
43 / 26468	28	06/08/2026	4820	Type 3
43 / 26469	28	06/08/2026	4960	Type 5

Average Strength (psi): 7 Day - 4310 psi, 28 Day - 4930 psi

06/09/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 44 **Sample #:** 7947 **Placement Date:** 05/12/2026 **Technician:** Jon Cross **Weather Conditions:** Sunny **Air Temp (°F):** 69

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Sidewalk, northbound lane on the side of Meridian Park Dr, going north to south, +/- 20' from Southeast corner of Meridian Park drive and Owl Place **Lat/Long:** 38.9460269 / -104.6086607

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
44	53 71414554	10.00	Slump: 5 1/4 Spec: 4 - 6	Result: 5 Spec.: 5 - 8	141.2	70	69

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
44 / 26365	7	05/19/2026	3850	Type 3

Average Strength (psi): 7 Day - 3850 psi

06/03/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 44 **Sample #:** 7947 **Placement Date:** 05/12/2026 **Technician:** Jon Cross **Weather Conditions:** Sunny **Air Temp (°F):** 69

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Sidewalk, northbound lane on the side of Meridian Park Dr, going north to south, +/- 20' from Southeast corner of Meridian Park drive and Owl Place **Lat/Long:** 38.9460269 / -104.6086607

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
44	53 71414554	10.00	Slump: 5 1/4 Spec: 4 - 6	Result: 5 Spec.: 5 - 8	141.2	70	69

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
44 / 26365	7	05/19/2026	3850	Type 3
44 / 26366	28	06/09/2026	4940	Type 2
44 / 26367	28	06/09/2026	5060	Type 3
44 / 26368	28	06/09/2026	4930	Type 3

Average Strength (psi): 7 Day - 3850 psi, 28 Day - 4980 psi

06/09/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 45 **Sample #:** 7960 **Placement Date:** 05/13/2026 **Technician:** Rodney Fannin **Weather Conditions:** Sunny **Air Temp (°F):** 60
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** At Station 3+50 along Merdian Park Drive. **Lat/Long:** 38.9445108 / -104.6087634

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
45	350 71414625	11.00	Slump: 6 Spec: 4 - 6	Result: 5.4 Spec.: 5 - 8	139.2	66	60

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
45 / 26566	7	05/20/2026	3460	Type 2

Average Strength (psi): 7 Day - 3460 psi

06/01/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 45 **Sample #:** 7960 **Placement Date:** 05/13/2026 **Technician:** Rodney Fannin **Weather Conditions:** Sunny **Air Temp (°F):** 60
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** At Station 3+50 along Merdain Park Drive. **Lat/Long:** 38.9445108 / -104.6087634

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
45	350 71414625	11.00	Slump: 6 Spec: 4 - 6	Result: 5.4 Spec.: 5 - 8	139.2	66	60

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
45 / 26566	7	05/20/2026	3460	Type 2
45 / 26567	28	06/10/2026	4230	Type 3

Average Strength (psi): 7 Day - 3460 psi, 28 Day - 4230 psi

56 Day Breaks will be provided when available.

06/11/2026

Reviewed by: Dylan Gassmann, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 45 **Sample #:** 7960 **Placement Date:** 05/13/2026 **Technician:** Rodney Fannin **Weather Conditions:** Sunny **Air Temp (°F):** 60
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** At Station 3+50 along Merdain Park Drive. **Lat/Long:** 38.9445108 / -104.6087634

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
45	350 71414625	11.00	Slump: 6 Spec: 4 - 6	Result: 5.4 Spec.: 5 - 8	139.2	66	60

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
45 / 26566	7	05/20/2026	3460	Type 2
45 / 26567	28	06/10/2026	4230	Type 3
45 / 26568	56	07/08/2026	4600	Type 3
45 / 26569	56	07/08/2026	4770	Type 3

Average Strength (psi): 7 Day - 3460 psi, 28 Day - 4230 psi, 56 Day - 4690 psi

07/10/2026

Reviewed by: Austin Nossokoff



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 46 **Sample #:** 8415 **Placement Date:** 06/22/2026 **Technician:** Michael Crytser **Weather Conditions:** Sunny **Air Temp (°F):** 77
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** Sidewalk at first fire hydrant north of round about of falcon market pl east side of road **Lat/Long:** 38.9447213 / -104.6087477

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
46	33 86766741	10.00	Slump: 4 1/2 Spec: 4 - 6	Result: 5.2 Spec.: 5 - 8	143.2	80	77

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
46 / 27969	7	06/29/2026	3990	Type 3

Average Strength (psi): 7 Day - 3990 psi

06/30/2026

Reviewed by: Austin Nossokoff, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 46 **Sample #:** 8415 **Placement Date:** 06/22/2026 **Technician:** Michael Crytser **Weather Conditions:** Sunny **Air Temp (°F):** 77

Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Sidewalk at first fire hydrant north of round about of Falcon Market Pl east side of road **Lat/Long:** 38.9447213 / -104.6087477

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
46	33 86766741	10.00	Slump: 4 1/2 Spec: 4 - 6	Result: 5.2 Spec.: 5 - 8	143.2	80	77

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
46 / 27969	7	06/29/2026	3990	Type 3
46 / 27970	28	07/20/2026	4750	Type 2
46 / 27971	28	07/20/2026	5060	Type 2
46 / 27972	28	07/20/2026	5200	Type 2

Average Strength (psi): 7 Day - 3990 psi, 28 Day - 5010 psi

07/21/2026

Reviewed by: Austin Nossokoff



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 47 **Sample #:** 8427 **Placement Date:** 06/23/2026 **Technician:** Dillon Mercer **Weather Conditions:** Sunny / Windy **Air Temp (°F):** 75

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Sidewalk on West side of Meridian Rd, 30' West & 75' North of Northwest corner of Eastonville Rd. and Meridian Rd. **Lat/Long:** 38.94451176 / -104.60805535

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
47	80 71417060	10.00	Slump: 4 Spec: 3 - 5	Result: 5 Spec.: 5 - 8	140.2	72	75

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
47 / 27994	7	06/30/2026	3670	Type 2

Average Strength (psi): 7 Day - 3670 psi

07/01/2026

Reviewed by: Austin Nossokoff, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 47 **Sample #:** 8427 **Placement Date:** 06/23/2026 **Technician:** Dillon Mercer **Weather Conditions:** Sunny / Windy **Air Temp (°F):** 75

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Sidewalk on West side of Meridian Rd, 30' West & 75' North of Northwest corner of Eastonville Rd. and Meridian Rd. **Lat/Long:** 38.94451176 / -104.60805535

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
47	80 71417060	10.00	Slump: 4 Spec: 3 - 5	Result: 5 Spec.: 5 - 8	140.2	72	75

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
47 / 27994	7	06/30/2026	3670	Type 2
47 / 27995	28	07/21/2026	4570	Type 5
47 / 27996	28	07/21/2026	4680	Type 3
47 / 27997	28	07/21/2026	4640	Type 3

Average Strength (psi): 7 Day - 3670 psi, 28 Day - 4630 psi

07/22/2026

Reviewed by: Austin Nossokoff



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 48 **Sample #:** 8452 **Placement Date:** 06/24/2026 **Technician:** Rodney Fannin **Weather Conditions:** Cloudy **Air Temp (°F):** 62
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** STA 4+65, west sidewalk on Meridian Rd. **Lat/Long:** 38.9452776 / -104.6080111

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
48	349 71417136	10.00	Slump: 4 3/4 Spec: 3 - 7	Result: 6 Spec.: 5 - 8	139.6	76	62

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
48 / 28103	7	07/01/2026	3250	Type 3

Average Strength (psi): 7 Day - 3250 psi

07/02/2026

Reviewed by: Austin Nossokoff, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 48 **Sample #:** 8452 **Placement Date:** 06/24/2026 **Technician:** Rodney Fannin **Weather Conditions:** Cloudy **Air Temp (°F):** 62
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** STA 4+65, west sidewalk on Meridian Rd. **Lat/Long:** 38.9452776 / -104.6080111

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
48	349 71417136	10.00	Slump: 4 3/4 Spec: 3 - 7	Result: 6 Spec.: 5 - 8	139.6	76	62

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
48 / 28103	7	07/01/2026	3250	Type 3
48 / 28104	28	07/22/2026	4170	Type 2

Average Strength (psi): 7 Day - 3250 psi, 28 Day - 4170 psi

56 Day Breaks will be provided when available.

07/22/2026

Reviewed by: Austin Nossokoff



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 48 **Sample #:** 8452 **Placement Date:** 06/24/2026 **Technician:** Rodney Fannin **Weather Conditions:** Cloudy **Air Temp (°F):** 62
Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** STA 4+65, west sidewalk on Meridian Rd. **Lat/Long:** 38.9452776 / -104.6080111

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
48	349 71417136	10.00	Slump: 4 3/4 Spec: 3 - 7	Result: 6 Spec.: 5 - 8	139.6	76	62

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
48 / 28103	7	07/01/2026	3250	Type 3
48 / 28104	28	07/22/2026	4170	Type 2
48 / 28105	56	08/19/2026	4710	Type 3
48 / 28106	56	08/19/2026	4700	Type 2

Average Strength (psi): 7 Day - 3250 psi, 28 Day - 4170 psi, 56 Day - 4700 psi

08/26/2026

Reviewed by: Austin Nossokoff



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 49 **Sample #:** 8469 **Placement Date:** 06/25/2026 **Technician:** Jacob Gammill **Weather Conditions:** Sunny / Partly Cloudy **Air Temp (°F):** 70

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Starting 75's from the intersection of owl pl and meridian going north then turning west for another 25' **Lat/Long:** 38.9456863 / -104.6080212

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
49	43 71417202	10.00	Slump: 4 Spec: 3 - 7	Result: 5.5 Spec.: 5 - 8	35.3	80	70

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
49 / 28180	7	07/02/2026	4080	Type 3

Average Strength (psi): 7 Day - 4080 psi

07/10/2026

Reviewed by: Austin Nossokoff



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 49 **Sample #:** 8469 **Placement Date:** 06/25/2026 **Technician:** Jacob Gammill **Weather Conditions:** Sunny / Partly Cloudy **Air Temp (°F):** 70

Contractor: Pyramid **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Starting 75's from the intersection of Owl Pl and Meridian going north then turning west for another 25' **Lat/Long:** 38.9456863 / -104.6080212

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
49	43 71417202	10.00	Slump: 4 Spec: 3 - 7	Result: 5.5 Spec.: 5 - 8	141.2	80	70

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
49 / 28180	7	07/02/2026	4080	Type 3
49 / 28194	28	07/23/2026	5180	Type 2
49 / 28195	28	07/23/2026	5050	Type 2
49 / 28196	28	07/23/2026	5080	Type 2

Average Strength (psi): 7 Day - 4080 psi, 28 Day - 5100 psi

07/23/2026

Reviewed by: Austin Nossokoff



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 50 **Sample #:** 8483 **Placement Date:** 06/26/2026 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 67

Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Sidewalk section at northwest corner of Meridian Rd. and Eastonville Rd. **Lat/Long:** 38.9444016 / -104.6082785

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
50	28 71417287	10.00	Slump: 5 Spec: 3 - 7	Result: 5.5 Spec.: 5 - 8	138.0	82	67

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
50 / 28228	10	07/03/2026	3370	Type 3

Average Strength (psi): 10 Day - 3370 psi

07/07/2026

Reviewed by: Austin Nossokoff, PE



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 50 **Sample #:** 8483 **Placement Date:** 06/26/2026 **Technician:** Kirby Hooker **Weather Conditions:** Sunny **Air Temp (°F):** 67

Contractor: Concrete Concepts Design **Supplier:** Amrize **Mix Design:** T34592110 **Specified Strength (psi):** 4500

Placement Location: Sidewalk **Location Details:** Sidewalk section at northwest corner of Meridian Rd. and Eastonville Rd. **Lat/Long:** 38.9444016 / -104.6082785

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
50	28 71417287	10.00	Slump: 5 Spec: 3 - 7	Result: 5.5 Spec.: 5 - 8	138.0	82	67

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
50 / 28228	10	07/03/2026	3370	Type 3
50 / 28229	28	07/24/2026	4420	Type 2
50 / 28230	28	07/24/2026	4580	Type 2
50 / 28231	28	07/24/2026	4300	Type 2

Average Strength (psi): 10 Day - 3370 psi, 28 Day - 4430 psi

07/27/2026

Reviewed by: Austin Nossokoff



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 51 **Sample #:** 8766 **Placement Date:** 07/21/2026 **Technician:** Matt Spring **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 85
Contractor: Pyramid **Supplier:** Pete Lien **Mix Design:** 902250 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** South west corner of Owl Place and Meridian Park **Lat/Long:** 38.9461117 / -104.6092198

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
51	20-00330 210384	4.50	Slump: 3 1/2 Spec: 3 - 7	Result: 5.5 Spec.: 5 - 8	142.0	90	85

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
51 / 29045	7	07/28/2026	4470	Type 2

Average Strength (psi): 7 Day - 4470 psi

07/30/2026

Reviewed by: Austin Nossokoff



Entech Engineering
505 Elkton Dr
Colorado Springs, CO 80907
Phone: 719-531-5599

Concrete Test

Client:

CD Meridian and Owl LLC c/o DSI
PO Box 50822
Colorado Springs, CO 80919

Project:

240809
Owl Marketplace
Meridian Rd north of King Soopers
Peyton, CO

Set #: 51 **Sample #:** 8766 **Placement Date:** 07/21/2026 **Technician:** Matt Spring **Weather Conditions:** Partly Cloudy **Air Temp (°F):** 85
Contractor: Pyramid **Supplier:** Pete Lien **Mix Design:** 902250 **Specified Strength (psi):** 4500
Placement Location: Sidewalk **Location Details:** South west corner of Owl Place and Meridian Park **Lat/Long:** 38.9461117 / -104.6092198

PLACEMENT DATA

Set #	Truck # Ticket #	Load Vol (yd³)	Slump (in)	Air Content (%)	Unit Weight (lb/ft³)	Concrete Temp (°F)	Air Temp (°F)
51	20-00330 210384	4.50	Slump: 3 1/2 Spec: 3 - 7	Result: 5.5 Spec.: 5 - 8	142.0	90	85

STRENGTH DATA

Set / Test	Age (days)	Test Date	Strength (psi)	Fracture Pattern
51 / 29045	7	07/28/2026	4470	Type 2
51 / 29046	28	08/18/2026	5320	Type 2
51 / 29047	28	08/18/2026	5470	Type 2
51 / 29048	28	08/18/2026	5150	Type 2

Average Strength (psi): 7 Day - 4470 psi, 28 Day - 5320 psi

08/19/2026

Reviewed by: Austin Nossokoff