Novemeber 3, 2023



S R Land, LLC 20 Boulder Crescent, 1st Floor, Suite 100 Colorado Springs, Colorado 80903

Attn: Chaz Collins

Re: Pavement Design Recommendations Homestead North at Sterling Ranch Filing No. 3 El Paso County, Colorado Entech Job No. 230423

Dear Mr. Collins:

As requested, Entech Engineering, Inc. (Entech) obtained samples of the pavement subgrade soils from the roadways in Homestead North at Sterling Ranch Subdivision, Filing No. 3, in El Paso County, Colorado, refer to Figure 1. This letter presents the results of the subsurface soil investigation, laboratory testing, and provides pavement recommendations for the roadway sections within the filing.

Project Description

The roadways for this project consist of a section of Aspen Valley Road and the full extents of William Downing Drive and associated cul-de-sac, David Rudabaugh Drive and associated cul-de-sacs, and Jesse Evans Drive and associated cul-de-sacs, all within Filing No. 3. The roadways are located within a proposed residential neighborhood.

Subsurface Explorations and Laboratory Testing

Subsurface conditions at the project site were explored by 13 test borings, designated, TB-1 through TB-13, on October 13, 2023. The locations of the test borings are shown on the Site and Exploration Plan, Figure 2. The borings were drilled to depths of 5 and 10 feet below the existing ground surface (bgs). The drilling was performed using a truck-mounted, continuous flight auger drill rig supplied and operated by Entech. Descriptive boring logs of the subsurface conditions encountered during drilling are presented in Appendix A. Groundwater levels were measured in each of the open boreholes at the conclusion of drilling.

Soil and bedrock samples were obtained from the borings utilizing the Standard Penetration Test (ASTM D1586) using a split-barrel California sampler. Results of the Standard Penetration Test (SPT) are included on the boring logs in terms of N-values expressed in blows per foot (bpf). Soil and bedrock samples recovered from the borings were visually classified and recorded on the boring logs. The soil and bedrock classifications were later verified utilizing laboratory testing and grouped by soil type. The soil and bedrock type numbers are included on the boring logs. It should be understood that the soil and bedrock descriptions shown on the boring logs may vary between boring location and sample depths. It should also be noted that the lines of stratigraphic separation shown on the boring logs represent approximate boundaries between soil and bedrock types and the actual stratigraphic transitions may be more gradual or variable with location.

Water content testing (ASTM D2216) was performed on the samples recovered from the borings, and the results are shown on the boring logs. Grain-Size Analysis (ASTM D422) and Atterberg Limits testing (ASTM D4318) were performed on selected samples to assist in classifying the materials encountered in the borings. Soluble sulfate testing was performed on select soil



samples to evaluate the potential for below grade degradation of concrete due to sulfate attack. The laboratory testing results are summarized on Table B-1 and are presented in Appendix B.

Subgrade Conditions

Subsurface conditions along the proposed roadways consisted of silty and clayey sand and sand with silt fill (Soil Type 1), native silty sand (Soil Type 2), and sandstone bedrock (Soil Type 3). When classified as a soil, the sandstone classified as very dense silty sand or sand. Soil type and corresponding AASHTO soil classification are listed below:

- Soil Type 1: A-1-b, A-2-4, and A-2-6
- Soil Type 2: A-1-b, and A-2-4
- Soil Type 3: A-2-4 (sandstone)

Groundwater was not encountered in the test borings. Laboratory test results are presented in Appendix B and are summarized in Table B-1.

California Bearing Ratio (CBR) testing was performed on a representative sample of Soil Type 1 from TB-10 to determine the support characteristic of the subgrade soils for the roadway sections. The results of the CBR testing, are presented in Appendix B and summarized as follows:

Design Parameter	Value
Soil Type	1 – Silty Sand
CBR at 95%	20.02
Design CBR	10
Liquid Limit	NV
Plasticity Index	NP
Percent Passing 200	22.3
AASHTO Classification	A-1-b
Group Index	0
Unified Soils Classification	SM

Exhibit 1: Subsurface Laboratory Testing Summary

Pavement Design

The CBR testing was used to determine the design subgrade modulus for the roadway. The pavement sections were determined utilizing the El Paso County Pavement Design Criteria Manual. Traffic data is not available for the local roadways within Homestead North Filing 3; however, the cul-de-sacs are classified as local low volume roadways and the remainder of the roads classify as local roads. The El Paso County Pavement Design Criteria and Report provides default 18-kip equivalent single axle loading (ESAL) based street classifications. For design, a default ESAL value of 36,500 and 292,000 was used for the local low volume and local roadway designations, respectively.

Alternative pavement sections for asphalt supported on aggregate base course (ABC) or recycled concrete, and asphalt supported on cement stabilized subgrade (CTS) are provided. Design parameters used in the pavement analysis are presented in Exhibit 2.



EXINDIT Z. Pavement Design Paran	neters
Design Parameter	Value
Reliability	
Local Low Volume	80%
Local Road	85% 💆
Standard Deviation	0.45
Serviceability Loss (Δ psi)	2.0
Design CBR	10
Resilient Modulus - Soil Type 1	15,000 psi
Structural Coefficients	
HMA	0.44
ABC	0.11
Recycled Concrete	0.11
CTS	0.11

Exhibit 2. Devement Design Deremeters

Per ECM Appendix D Table D-1 the reliability value for a urban local road is 80%. Please revise.

The pavement design calculations are presented in Appendix C. Any additional grading may result in subgrade soils with different support characteristics. The following pavement sections should be re-evaluated if additional grading is performed. Pavement sections recommended for this phase of the filing are summarized in Exhibit 3.

Exhibit 3: Recommended Pavement Sections

Pavement Area	Design ESAL	Alternative
Low volume	36 500	1. 3.0 inches HMA over 6.0 inches ABC
Local Roads	30,300	2. 4.0 inches HMA over 10.0 inches of CTS
Loool Boodo	202.000	1. 3.0 inches HMA over 8.0 inches ABC
	292,000	2. 4.0 inches HMA over 10.0 inches of CTS

ABC = Aggregate Base Course; ESAL = equivalent single axle loads; HMA = Hot Mix Asphalt; CTS = Cement Treated Subgrade

Notes:

- 1. All pavement alternatives represent the minimum sections required per El
- Paso County Pavement Design Criteria Manual.
- 2. Full depth sections are not recommended by El Paso County.

Swelling Soils Mitigation

El Paso County criteria requires mitigation of expansive soils for roadway subgrade that have a swell of 2 percent or greater with a 150 pound per square foot surcharge. Based on the classification of the subgrade soils, mitigation for expansive soils is not required on this site.



Roadway Construction – Full Depth Asphalt and Asphalt on Aggregate Basecourse Alternatives

If pavement section alternatives are selected utilizing ABC, the final subgrade surface should be scarified to a depth of 12 inches, moisture conditioned within +/-2% of the optimum water content, and recompacted to 95% of its maximum Modified Proctor dry density, ASTM D1557.

The compacted surface below pavements should be proof-rolled with a fully loaded, tandem-axle, 10-yard dump truck or equivalent. Any areas that are delineated to be soft, loose, or yielding during proof-rolling should be removed and reconditioned or replaced.

ABC materials shall conform to the Table D-6 from the El Paso County Pavement Design Criteria and Report. ABC materials should be compacted to a minimum of 95% of its maximum Modified Proctor Dry Density (ASTM D1557) at +/-2% of optimum moisture content.

Roadway Construction – Stabilized Subgrade Alternative

Prior to placement of the asphalt, the subgrade shall be stabilized by the addition of cement to a depth of at least 10 inches if CTS alternatives are selected. The amount of cement applied shall be a minimum of 2% (by weight) of the subgrade's maximum dry density as determined by the Modified Proctor Test (ASTM D1557) or by the Standard Proctor Test (ASTM D698). Local practice typically recommends that the design mix be increased by 1% in the field to account for waste and construction variability. The cement should be spread evenly on the subgrade surface and be thoroughly mixed into the subgrade over a 10-inch depth, as specified, such that a uniform blend of soil and cement is achieved. Prior to application or mixing of the cement the upper 10 inches of subgrade should be thoroughly moisture conditioned to the soil's optimum water content or as much as 2% more than the optimum water content as necessary to provide a compactable soil condition. Densification of the cement-stabilized subgrade should be completed to obtain a compaction of at least 95% of the subgrade maximum dry density as determined by the Modified Proctor Test (ASTM D1557) or by the Standard Proctor Test (ASTM D698). Satisfactory compaction of the subgrade shall be count of mixing the cement into the subgrade.

The following conditions shall be observed as part of the subgrade stabilization:

- Type I/II cement as supplied; a local supplier shall be used. All cement used for stabilization should come from the same source. If cement sources are changed a new laboratory mix design should be completed.
- Moisture conditioning of the subgrade and/or mixing of the cement into the subgrade shall not occur when soil temperatures are below 40° F. Cement-treated subgrades should be maintained at a temperature of 40° F or greater until the subgrade has been compacted as required.
- Cement placement, cement mixing, and compaction of the cement-treated subgrade should be observed by a qualified geotechnical engineer. The geotechnical engineer should complete in-situ compaction tests and construct representative compacted specimens of the treated subgrade material for subsequent laboratory quality assurance testing.
- Pending the results of the field density testing, microfracturing of the stabilized subgrade may be required. Soil strengths in excess of 275 psi require microfracturing.

In addition to the above guidance, the asphalt, cement, subgrade conditions, compaction of materials and roadway construction methods shall meet the El Paso County Pavement Design Criteria and the Pikes Peak Region Asphalt Paving Specifications.



We trust that this report contains the information you require. If you have questions or need additional information, please contact us.

Respectfully Submitted,

ENTECH ENGINEERING, INC.

Daniel P. Stegman Geotechnical Engineering Staff

Reviewed by:



Joseph C. Goode III, P.E. Sr. Engineer

Encl.

SW:JCG/jcg AAProjects/2023/230423/ssi

If proposing CTS please provide a laboratory CTS mix design and test results showing that test criteria for CTS with a strength coefficient of 0.11 is met. (7 day, 125 psi)

Per ECM Appendix D.6 please provide the following:

• Scaled drawings showing the estimated extent of subgrade soil types and ESAL for each roadway.

• Pavement design alternatives for each roadway on a scaled drawing.





VICINITY MAP

HOMESTEAD NORTH F3 SR LAND, LLC JOB NO. 230423

FIG. 1



APPENDIX A: Test Boring Logs

TEST BORING 1 DATE DRILLED 10/13/20	23					TEST BORING 2 DATE DRILLED 10/13/20	2)23			
REMARKS	epth (ft) mbol	tmples	ows per foot	atercontent %	il Type	REMARKS	spth (ft) mbol mples	ows per foot	atercontent %	il Type
DRY TO 10', 10/13/23 FILL 0-7', SAND, SILTY, BROWN, MEDIUM DENSE, MOIST		Sa Sa	<u>9</u> 20 20	6.3 6.1	<u>0</u> 1	DRY TO 5', 10/13/23 FILL 0-5', SAND, WITH SILT, BROWN, MEDIUM DENSE, MOIST		표 23 21	5.6 8.8	0 <u>0</u> 1
SAND, SILTY, TAN, MEDIUM DENSE, MOIST			24	6.9	2					
	20						13 - - 20			
						TEST BORING LOG	S No. 3	, ,	JOB N 2304	\O. 23 ∆_1
	G, INC				ŀ	TEST BORING LOG	S No. 3	, F	JOB 1 2304 FIG.	

TEST BORING 3	22						TEST BORING 4	22				
REMARKS	23					1	REMARKS		1			
DRY TO 5', 10/13/23	Depth (ft)	Symbol	Samples	Blows per foot	Watercontent %	Soil Type	DRY TO 10', 10/13/23	Depth (ft) Symbol	Samples	Blows per foot	Watercontent %	Soil Type
FILL 0-5', SAND, WITH SILT,							FILL 0-8', SAND, WITH SILT,				-	
BROWN, MEDIUM DENSE, MOIST	-	 		27	8.8	1	BROWN, MEDIUM DENSE, MOIST		•	21	6.2	1
	5			24	7.7	1		5		26	11.8	1
	10						SAND, SILTY, TAN, DENSE, MOIST			43	6.5	2
	15							15				
	20							20				
	-							-				
ENTECH								S			JOB N 2304	NO. 23

HOMESTEAD NORTH, FILING No. 3 SR LAND

IEST BORING 5	^ 2						TEST BORING 6) 100					
BEMARKS	23						REMARKS	123		I			
DRY TO 5', 10/13/23	Depth (ft)	Symbol	Samples	Blows per foot	Watercontent %	Soil Type	DRY TO 5', 10/13/23	Depth (ft)	Symbol	Samples	Blows per foot	Watercontent %	Soil Type
FILL 0-4', SAND, CLAYEY, BROWN,	_	·		10	60	1	FILL 0-4', SAND, SILTY, BROWN,	-			26	10	1
MEDIUM DENSE, MOIST	-			10	0.9		MEDIUM DENSE, MOIST	-		_	20	4.2	
SAND, SILTY, TAN, MEDIUM DENSE, DRY	5			19	0.9	1	SAND, SILTY, TAN, MEDIUM DENSE, DRY	5			26	2.2	2
	10							10					
	-							-					
	-							-					
	15							15					
	-							-					
		1											
	20							20					
		1							1				



TEST BORING LOGS

HOMESTEAD NORTH, FILING No. 3 SR LAND JOB NO. 230423

TEST BORING 7 DATE DRILLED 10/13/20	23						TEST BORING 8 DATE DRILLED 10/13/2023				
REMARKS DRY TO 5', 10/13/23 FILL 0-9', SAND, CLAYEY, BROWN, MEDIUM DENSE, MOIST	Gepth (ft)	Symbol Symbol	Samples	21 Blows per foot	0.01 Watercontent %	L L Soil Type	REMARKS Image: strain of the	 Watercontent % Type 			
SAND, SILTY, BROWN, MEDIUM DENSE, MOIST	10 15 20			19	18.5	2					
			I			F	TEST BORING LOGS	JOB NO. 230423			
ENGINEERING, INC.							SR LAND	FIG. A-4			

TEST BORING 9 DATE DRILLED 10/13/20) 123						TEST BORING 10 DATE DRILLED 10/13/2023		
DRY TO 5', 10/13/23 FILL 0-5', SAND, WITH SILT, BROWN, MEDIUM DENSE, MOIST	10 15 20	Symbol	Samples	1 1 Blows per foot	% Matercontent % 2.4	L L Soil Type	DATE DRILLED 10/13/2023 REMARKS Image: Construction of the second secon	9. Content % Matercontent %	1 1 Soil Type
	C G, I	N C	l			F	TEST BORING LOGS HOMESTEAD NORTH, FILING No. 3 SR LAND	JOB 2304 FIG.	NO. 123 A-5

TEST BORING 11							TEST BORING 12	2					
DATE DRILLED 10/13/202	23	-		-		1	DATE DRILLED 10/13/20	23					
	epth (ft)	ymbol	amples	lows per foot	/atercontent %	oil Type		epth (ft)	ymbol	amples	lows per foot	/atercontent %	oil Type
DRY TO 5', $10/13/23$		́О́	ŝ	В	>	Ň	DRY TO 10', 10/13/23		Ś	ŝ	Β	\$	Ň
DENSE, MOIST	-			35	8.2	1	MEDIUM DENSE to LOOSE, MOIST	-			11	7.2	1
SANDSTONE, EXTREMELY WEAK, TAN, HIGHLY WEATHERED (SAND, SILTY, VERY DENSE, MOIST)	5			<u>50</u> 10"	6.2	3		5			9	8.2	1
	10						SANDSTONE, EXTREMELY WEAK, TAN, HIGHLY WEATHERED (SAND, SILTY, VERY DENSE, MOIST)	10			<u>50</u> 10"	4.3	3
	15							15					
	20							20					



TEST BORING LOGS

HOMESTEAD NORTH, FILING No. 3 SR LAND JOB NO. 230423

TEST BORING13DATE DRILLED10/13/202	23					
REMARKS	Jepth (ft)	symbol	Samples	slows per foot	Vatercontent %	soil Type
			0)	ш	>	0)
BROWN, MEDIUM DENSE, MOIST	-			12	4.0	1
	5			12	4.2	1
	-					
	10					
	-					
	15					
	20					



TEST BORING LOGS

HOMESTEAD NORTH, FILING No. 3 SR LAND JOB NO. 230423

APPENDIX B: Laboratory Test Results



 TABLE B-1

 SUMMARY OF LABORATORY TEST RESULTS

SOIL TYPE	TEST BORING NO.	DEPTH (FT)	PASSING NO. 200 SIEVE (%)	LIQUID LIMIT	PLASTIC LIMIT	PLASTIC INDEX	SULFATE (WT %)	AASHTO CLASS.	USCS	SOIL DESCRIPTION
1, CBR	10	0-3	22.3	NV	NP	NP		A-1-b	SM	FILL, SANDY, SILTY
1	1	1-2	21.6	NV	NP	NP		A-1-b	SM	FILL, SANDY, SILTY
1	2	1-2	6.5	NV	NP	NP		A-1-b	SW-SM	FILL, SAND, WITH SILT
1	3	1-2	7.8	NV	NP	NP		A-1-b	SW-SM	FILL, SAND, WITH SILT
1	4	1-2	8.6	NV	NP	NP	<0.01	A-1-b	SW-SM	FILL, SAND, WITH SILT
1	5	1-2	21.7	31	18	13		A-2-6	SC	FILL, SANDY, CLAYEY
1	6	1-2	24.8	NV	NP	NP		A-1-b	SM	FILL, SANDY, SILTY
1	7	1-2	17.3	30	18	12	<0.01	A-2-6	SC	FILL, SANDY, CLAYEY
1	8	1-2	6.8	NV	NP	NP		A-1-b	SW-SM	FILL, SAND, WITH SILT
1	9	1-2	6.0	NV	NP	NP		A-1-b	SW-SM	FILL, SAND, WITH SILT
1	10	1-2	8.0	NV	NP	NP		A-1-b	SW-SM	FILL, SAND, WITH SILT
1	11	1-2	13.1	NV	NP	NP	0.03	A-2-4	SM	FILL, SANDY, SILTY
1	12	1-2	18.4	NV	NP	NP		A-1-b	SM	FILL, SANDY, SILTY
1	13	1-2	5.2	NV	NP	NP		A-1-b	SW-SM	FILL, SAND, WITH SILT

TEST BORING 10 DEPTH (FT) 0-3

SOIL DESCRIPTION FILL, SANDY, SILTY SOIL TYPE 1, CBR



GRAIN SIZE ANALYSIS

U.S.	Percent
<u>Sieve #</u>	<u>Finer</u>
3"	
1 1/2"	
3/4"	
1/2"	
3/8"	100.0%
4	96.5%
10	85.8%
20	67.6%
40	41.7%
100	25.8%
200	22.3%

SOIL CLASSIFICATION

USCS CLASSIFICATION:	SM
AASHTO CLASSIFICATION:	A-1-b
AASHTO GROUP INDEX:	0

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND



SOIL DESCRIPTION FILL, SANDY, SILTY SOIL TYPE 1



GRAIN SIZE ANALYSIS

U.S.	Percent
Sieve #	<u>Finer</u>
3"	
1 1/2"	
3/4"	
1/2"	
3/8"	100.0%
4	91.8%
10	73.6%
20	54.3%
40	43.1%
100	28.5%
200	21.6%

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

SOIL CLASSIFICATION

USCS CLASSIFICATION:	SM
AASHTO CLASSIFICATION:	A-1-b
AASHTO GROUP INDEX:	0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND



1

Grain size (mm)

GRAIN SIZE ANALYSIS

10

30%

20%

10%

0%

100

U.S.	Percent
<u>Sieve #</u>	Finer
3"	
1 1/2"	
3/4"	
1/2"	100.0%
3/8"	98.0%
4	86.4%
10	61.7%
20	40.6%
40	28.9%
100	11.5%
200	6.5%

ATTERBERG LIMITS

#40

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

#100

0.1

#200

0.01

SOIL CLASSIFICATION

USCS CLASSIFICATION: SW-SM AASHTO CLASSIFICATION: A-1-b AASHTO GROUP INDEX: 0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND

TEST BORING	3	SOIL DESCRIPTION FILL, SAND, WITH SILT
DEPTH (FT)	1-2	SOIL TYPE 1



0.5.	Percent
Sieve #	Finer
3"	
1 1/2"	
3/4"	
1/2"	100.0%
3/8"	99.0%
4	92.1%
10	53.6%
20	24.8%
40	16.1%
100	9.8%
200	7.8%

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

SOIL CLASSIFICATION

USCS CLASSIFICATION: SW-SM AASHTO CLASSIFICATION: A-1-b AASHTO GROUP INDEX: 0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND





U.S.	Percent
Sieve #	<u>Finer</u>
3"	
1 1/2"	
3/4"	
1/2"	100.0%
3/8"	92.3%
4	84.7%
10	59.5%
20	36.8%
40	24.6%
100	12.4%
200	8.6%

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

SOIL CLASSIFICATION

USCS CLASSIFICATION: SW-SM AASHTO CLASSIFICATION: A-1-b AASHTO GROUP INDEX: 0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND



Grain size (mm)

GRAIN SIZE ANALYSIS

U.S.	Percent
Sieve #	<u>Finer</u>
3"	
1 1/2"	
3/4"	
1/2"	100.0%
3/8"	94.7%
4	88.7%
10	70.6%
20	52.2%
40	41.9%
100	28.2%
200	21.7%

SOIL CLASSIFICATION

USCS CLASSIFICATION:	SC
AASHTO CLASSIFICATION:	A-2-6
AASHTO GROUP INDEX:	0

ENGINEERING, INC.

ATTERBERG LIMITS

Plastic Limit	18
Liquid Limit	31
Plastic Index	13

LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND



Percent
Finer
100.0%
98.6%
90.4%
74.0%
56.1%
45.5%
31.5%
24.8%

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

SOIL CLASSIFICATION

USCS CLASSIFICATION:	SM
AASHTO CLASSIFICATION:	A-1-b
AASHTO GROUP INDEX:	0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND





U.S.	Percent
Sieve #	Finer
3"	
1 1/2"	
3/4"	
1/2"	
3/8"	100.0%
4	93.7%
10	70.1%
20	49.2%
40	37.8%
100	23.5%
200	17.3%

ATTERBERG LIMITS

Plastic Limit	18
Liquid Limit	30
Plastic Index	12

SOIL CLASSIFICATION

USCS CLASSIFICATION:	SC
AASHTO CLASSIFICATION:	A-2-6
AASHTO GROUP INDEX:	0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND



Grain size (mm)

1

GRAIN SIZE ANALYSIS

100

10

U.S.	Percent
Sieve #	Finer
3"	
1 1/2"	
3/4"	
1/2"	
3/8"	100.0%
4	92.8%
10	69.6%
20	52.7%
40	39.7%
100	14.3%
200	6.8%

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

0.1

SOIL CLASSIFICATION

USCS CLASSIFICATION: SW-SM AASHTO CLASSIFICATION: A-1-b AASHTO GROUP INDEX: 0



LABORATORY TEST RESULTS

JOB NO. 230423

0.01

HOMESTEAD NORTH, FILING No. 3 SR LAND





U.S.	Percent
Sieve #	<u>Finer</u>
3"	
1 1/2"	
3/4"	
1/2"	100.0%
3/8"	96.5%
4	79.4%
10	56.2%
20	37.1%
40	23.7%
100	8.9%
200	6.0%

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

SOIL CLASSIFICATION

USCS CLASSIFICATION: SW-SM AASHTO CLASSIFICATION: A-1-b AASHTO GROUP INDEX: 0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND

TEST BORING	10	SOIL DESCRIPTION FILL, SAND, WITH SILT
<u>DEPTH (FT)</u>	1-2	SOIL TYPE 1



U.S.	Percent
Sieve #	<u>Finer</u>
3"	
1 1/2"	
3/4"	
1/2"	100.0%
3/8"	90.7%
4	79.7%
10	49.2%
20	30.8%
40	23.6%
100	11.5%
200	8.0%

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

SOIL CLASSIFICATION

USCS CLASSIFICATION: SW-SM AASHTO CLASSIFICATION: A-1-b AASHTO GROUP INDEX: 0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND



U.S.	Percent
<u>Sieve #</u>	Finer
3"	
1 1/2"	
3/4"	
1/2"	
3/8"	100.0%
4	98.3%
10	90.1%
20	70.0%
40	52.8%
100	19.3%
200	13.1%

SOIL CLASSIFICATION	
USCS CLASSIFICATION:	SM
AASHTO CLASSIFICATION:	A-2-4
AASHTO GROUP INDEX:	0

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND



Grain size (mm)

GRAIN SIZE ANALYSIS

Percent
<u>Finer</u>
100.0%
93.7%
71.0%
51.2%
38.9%
24.2%
18.4%

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

SOIL CLASSIFICATION

USCS CLASSIFICATION:	SM
AASHTO CLASSIFICATION:	A-1-b
AASHTO GROUP INDEX:	0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND

TEST BORING	13	SOIL DESCRIPTION FILL, SAND, WITH SILT
<u>DEPTH (FT)</u>	1-2	SOIL TYPE 1



U.S.	Percent
<u>Sieve #</u>	<u>Finer</u>
3"	
1 1/2"	
3/4"	
1/2"	100.0%
3/8"	96.8%
4	75.3%
10	45.1%
20	25.4%
40	14.5%
100	6.6%
200	5.2%

ATTERBERG LIMITS

Plastic Limit	NP
Liquid Limit	NV
Plastic Index	NP

SOIL CLASSIFICATION

USCS CLASSIFICATION: SW-SM AASHTO CLASSIFICATION: A-1-b AASHTO GROUP INDEX: 0



LABORATORY TEST RESULTS

JOB NO. 230423

HOMESTEAD NORTH, FILING No. 3 SR LAND



SAMPLE LOCATION TB-10 @ 0-3'

SOIL DESCRIPTION SAND, SILTY, BROWN SOIL TYPE 1

CBR TEST LOAD DATA

Piston Diameter (cm): 4.958 Piston Area (in²): 2.993

	10 BLOWS		25 BLOWS		56 BLOWS	
Penetration	Mold # 1		Mold # 2		Mold # 3	
Depth	Load	Stress	Load	Stress	Load	Stress
(inches)	(lbs)	(psi)	(lbs)	(psi)	(lbs)	(psi)
0.000	0	0.00	0	0.00	0	0.00
0.025	204	68.17	320	106.93	330	110.28
0.050	291	97.24	512	171.09	551	184.13
0.075	337	112.61	641	214.20	721	240.93
0.100	385	128.65	810	270.68	917	306.43
0.125	419	140.02	968	323.47	1103	368.59
0.150	455	152.05	1107	369.92	1311	438.09
0.175	497	166.08	1281	428.07	1478	493.90
0.200	527	176.11	1439	480.87	1659	554.38
0.300	668	223.22	2239	748.20	2587	864.49
0.400	794	265.33	2805	937.34	3261	1089.72
0.500	934	312.11	3417	1141.85	4181	1397.16

MOISTURE AND DENSITY DATA

	Mold # 1	Mold # 2	Mold # 3
Can #	399	351	351
Wt. Can	8.43	8.46	7.88
Wt. Can+Wet	282.49	212.43	201.52
Wt. Can+Dry	251.19	190.53	182.59
Wt. H20	31.3	21.9	18.93
Wt. Dry Soil	242.76	182.07	174.71
Moisture Content	12.89%	12.03%	10.84%
Wet Density (PCF)	127.1	135.8	139.1
Dry Density (PCF)	118.4	126.5	129.5
% Compaction	92%	98%	100%
CBR	12.87	27.07	30.64

CBR at 90% of Max. Density =	8.72 ~ R VALUE 22	
CBR at 95% of Max. Density =	20.02 ~ R VALUE 71	

PROCTOR DATA

Maximum Dry Density (pcf)	128.9
Optimum Moisture	7.4
90% of Max. Dry Density (pcf)	116.0
95% of Max. Dry Density (pcf)	122.5

HOMESTEAD NORTH, FILING No. 3 SR LAND

LABORATORY TEST RESULTS

JOB NO. 230423



SOIL DESCRIPTION SAND, SILTY, BROWN SOIL TYPE 0



APPENDIX C: Pavement Design Calculations



PROJECT DATA





Layer	Material	Structural Layer	Thickne	$ess(D_i^*)$	SN* _i	SN
1	HMA	$C_1 = 0.44$	3.0	inches	1.320	
2	ABC	$C_2 = 0.11$	6.0	inches	0.660	-
				SN* =	1.980	1.38



PROJECT DATA

Project Location Homestead North Filing 3 - Local Low Volume Road Job Number: 230423



Layer	Material	Structural Layer	Thickne	$ess(D_i^*)$	SN* _i	SN
1	HMA	$C_1 = 0.44$	4.0	inches	1.760	
2	CTS	$C_2 = 0.11$	10.0	inches	1.100	-
				SN* =	2 860	1.44



PROJECT DATA

Project Location Homestead North Filing 3 - Local Road Job Number: 230423

DESIGN DATA



RECOMMENED THICKNESSES

Layer	Material	Structural Layer	Thickne	$ess(D_i^*)$	SN* _i	SN
1	HMA	$C_1 = 0.44$	3.0	inches	1.320	
2	ABC	$C_2 = 0.11$	8.0	inches	0.880	-
				SN* =	2 200	2.06



PROJECT DATA

Project Location Homestead North Filing 3 - Local Road Job Number: 230423

DESIGN DATA



RECOMMENED THICKNESSES

Layer	Material	Structural Layer	Thickness (D_{i}^{*})		SN* _i	SN
1	HMA	$C_1 = 0.44$	4.0	inches	1.760	
2	CTS	$C_2 = 0.11$	10.0	inches	1.100	-
				SN* =	2 860	2.06