



ENTECH
 ENGINEERING, INC.
 505 Elkton Drive
 Colorado Springs, CO 80907
 (719) 531-5599 • (719) 531-5238 (fax)

| | |
|--------------|--|
| Client: | FLRD #5 |
| Project: | Forest Lakes Residential Development, Filing 5 |
| Entech Job # | 192273 |

CONCRETE TEST

| | | | | | | | | |
|-----------------------|----------------|--------------------------|-------------------------|-------------------|-------------------|---------------------|--|--|
| PG | | | Test #: | | | 32 | | |
| Date: | # of Specimens | Specified Strength (psi) | Time of Test | Hours Field Cured | Lab Receive Date: | | | |
| 9/18/2020 | 4 | 4500 | 2:55 PM | 24 | 9/19/2020 | | | |
| Specimen Type | | | Test Type | | | Type of Cure | | |
| Cylinders 4x8 | | | Field | | | Tank | | |
| Contractor: | | | Supplier: | | | Mix Design Number | | |
| Ideal Concrete | | | Action Ready Mix | | | A45BD67FCG | | |
| Truck Number | | | Ticket Number | | | Batch Time: | | |
| 521 | | | 55768 | | | 1:45 PM | | |

Location:
 Curb and gutter on the north side of Forest Lakes Drive, 15' west off the northwest corner of Lot 6, at (39.059810, -104.896645)

| | | | | |
|--------------|----------|--------------------|--------------------|---------------|
| Slump (in.): | Air (%): | Unit Weight (PCF): | Concrete Temp (°F) | Air Temp (°F) |
| 2.0 | 5.2 | 143.4 | 80 | 76 |

| 7-Day Strength | 28-Day Strength | -Day Strength | 56-Day Strength | -Day Strength |
|----------------|-----------------|---------------|-----------------|---------------|
| 3800 | 4820 | | | |
| | 5120 | | | |
| | | | | |
| Average: | Average: | Average: | Average: | Average: |
| 3800 | 4970 | | | |
| Break Date: | Break Date: | Break Date: | Break Date: | Break Date: |
| 9/25/2020 | 10/16/2020 | | | |

Remarks:
28 Day Results

Specifications: 4500 PSI, 5-8% Air, 4" Max Slump
 Break Sequence: 1@7, 2@28, 1@hold

Summary Comments:
Ideal Concrete, Action Ready Mix

Reviewed By: *R.P.J.*

