



ENTECH
 ENGINEERING, INC.
 505 Elkton Drive
 Colorado Springs, CO 80907
 (719) 531-5599 • (719) 531-5238 (fax)

Client:	FLRD #5
Project:	Forest Lakes Residential Development, Filing 5
Entech Job #	192273

CONCRETE TEST

TG			Test #: 37		
Date: 10/1/2020	# of Specimens: 4	Specified Strength (psi): 4500	Time of Test: 10:10 AM	Hours Field Cured: 24	Lab Receive Date: 10/2/2020
Specimen Type		Test Type		Type of Cure	
Cylinders 4x8		Field		Tank	
Contractor: Ideal Concrete		Supplier: Action Ready Mix		Mix Design Number: A45BD67F	
Truck Number: 531		Ticket Number: 56405		Batch Time: 9:08 AM	

Location:
 Curb and gutter, south side of Mesa Top Drive (39.0615714, -104.9012033)

Slump (in.): 4.0	Air (%): 7.4	Unit Weight (PCF): 140.2	Concrete Temp (°F): 70	Air Temp (°F): 41
------------------	--------------	--------------------------	------------------------	-------------------

7-Day Strength	28-Day Strength	-Day Strength	56-Day Strength	-Day Strength
3350				
Average: 3350	Average:	Average:	Average:	Average:
Break Date: 10/8/2020	Break Date: 10/29/2020	Break Date:	Break Date:	Break Date:

Remarks:
 7 Day Results

Specifications: 4500 PSI, 5-8% Air, 4" Max Slump	Break Sequence: 1@7, 2@28, 1@hold
--	-----------------------------------

Summary Comments:
 Ideal Concrete, Action Ready Mix

Reviewed By: *RPJ*