



ENTECH
 ENGINEERING, INC.
 505 Elkton Drive
 Colorado Springs, CO 80907
 (719) 531-5599 • (719) 531-5238 (fax)

Client:	FLRD #5
Project:	Forest Lakes Residential Development, Filing 5
Entech Job #	192273

CONCRETE TEST

PG			Test #:			23		
Date:	# of Specimens	Specified Strength (psi)	Time of Test	Hours Field Cured	Lab Receive Date:			
8/26/2020	4	4500	1:10 PM	24	8/27/2020			
Specimen Type			Test Type			Type of Cure		
Cylinders 4x8			Field			Tank		
Contractor:			Supplier:			Mix Design Number		
PPC Construction			Pete Lien			90DJ50		
Truck Number			Ticket Number			Batch Time:		
2277			975081			12:02 PM		

Location:
 Lids for outlets, Lots 9 & 10 (north lid).

Slump (in.):	Air (%):	Unit Weight (PCF):	Concrete Temp (°F)	Air Temp (°F)
4.0	6.1	139.0	85	85

7-Day Strength	28-Day Strength	-Day Strength	56-Day Strength	-Day Strength
4520	5260			
	5080			
Average:	Average:	Average:	Average:	Average:
4520	5170			
Break Date:	Break Date:	Break Date:	Break Date:	Break Date:
9/2/2020	9/23/2020			

Remarks:
 28 Day Results

Specifications:	Break Sequence:
4500 PSI, 4" Max Slump, 4.5-7.5% Air	1@7, 2@28, 1@hold

Summary Comments:
 PPC Construction, Pete Lien

Reviewed By: *RPJ*

