



ENTECH
 ENGINEERING, INC.
 505 Elkton Drive
 Colorado Springs, CO 80907
 (719) 531-5599 • (719) 531-5238 (fax)

Client:	FLRD #5
Project:	Forest Lakes Residential Development, Filing 5
Entech Job #	192273

CONCRETE TEST

JB			Test #: 38		
Date:	# of Specimens	Specified Strength (psi)	Time of Test	Hours Field Cured	Lab Receive Date:
10/2/2020	4	4500	10:40 AM	24	10/3/2020
Specimen Type		Test Type		Type of Cure	
Cylinders 4x8		Field		Tank	
Contractor:		Supplier:		Mix Design Number	
Ideal Concrete		Action Ready Mix		4500-CDOT	
Truck Number		Ticket Number		Batch Time:	
514				10:00 AM	

Location
 Curb and Gutter, 10' S. off SE corner of intersction of Forest Lakes Dr. and Mesa Top Dr.

Slump (in.)	Air (%):	Unit Weight (PCF):	Concrete Temp (°F)	Air Temp (°F)
3.75	5.4	143.8	73	77
7-Day Strength	28-Day Strength	-Day Strength	56-Day Strength	-Day Strength
3850				
Average:	Average:	Average:	Average:	Average:
3850				
Break Date:	Break Date:	Break Date:	Break Date:	Break Date:
10/9/2020	10/30/2020			

Remarks:
 7 Day Results

Specifications: 4500 PSI, 5-8% Air, 3-5" Slump	Break Sequence: 1@7, 2@28, 1@hold
---	--------------------------------------

Summary Comments:
 Ideal Concrete, Action Ready Mix

Reviewed By: *RPJ*