



**ENTECH**  
 ENGINEERING, INC.  
 505 Elkton Drive  
 Colorado Springs, CO 80907  
 (719) 531-5599 • (719) 531-5238 (fax)

Client: **FLRD #5**  
 Project: **Forest Lakes Residential Development, Filing 5**  
 Entech Job # **192273**

**CONCRETE TEST**

<b>EO</b>			Test #:			<b>36</b>		
Date:	# of Specimens	Specified Strength (psi)	Time of Test	Hours Field Cured	Lab Receive Date:			
9/23/2020	4	4500	12:30 PM	24	9/24/2020			
<b>Specimen Type</b>		<b>Test Type</b>		<b>Type of Cure</b>				
<b>Cylinders 4x8</b>		<b>Field</b>		<b>Tank</b>				
Contractor:		Supplier:		Mix Design Number				
<b>Ideal Concrete</b>		<b>Action Ready Mix</b>		<b>A45BD67FCG</b>				
Truck Number		Ticket Number		Batch Time:				
<b>522</b>		<b>55997</b>		<b>11:08 AM</b>				

Location  
 Curb and gutter, south half of median on Mesa Top Drive (39.0607714, -104.9005274)

Slump (in.)	Air (%):	Unit Weight (PCF):	Concrete Temp (°F)	Air Temp (°F)
1.75	6.0	141.2	83	72

7-Day Strength	28-Day Strength	-Day Strength	56-Day Strength	-Day Strength
3910	4790			
	4700			
Average:	Average:	Average:	Average:	Average:
3910	4750			
Break Date:	Break Date:	Break Date:	Break Date:	Break Date:
9/30/2020	10/21/2020			

Remarks:  
**28 Day Results**

Specifications: 4500 PSI, 5-8% Air, 4" Max Slump  
 Break Sequence: 1 @ 7, 2 @ 28, 1 @ hold

Summary Comments:  
**Ideal Concrete, Action Ready Mix**

Reviewed By: *R.P.J.*

