



ENTECH
 ENGINEERING, INC.
 505 Elkton Drive
 Colorado Springs, CO 80907
 (719) 531-5599 • (719) 531-5238 (fax)

Client:	FLRD #5
Project:	Forest Lakes Residential Development, Filing 5
Entech Job #	192273

CONCRETE TEST

PG			Test #: 27		
Date:	# of Specimens	Specified Strength (psi)	Time of Test	Hours Field Cured	Lab Receive Date:
9/17/2020	4	4500	1:55 PM	24	9/18/2020
Specimen Type		Test Type		Type of Cure	
Cylinders 4x8		Field		Tank	
Contractor:		Supplier:		Mix Design Number	
Ideal Concrete		Action Ready Mix		A45BD67FCG	
Truck Number		Ticket Number		Batch Time:	
529		55679		12:43 PM	

Location:
 Curb and gutter, on the north side of Mesa Top Drive, 12' east off Lot 14 on Mesa Top Drive, at 39.060865, -104.898699

Slump (in.):	Air (%):	Unit Weight (PCF):	Concrete Temp (°F)	Air Temp (°F)
2.25	5.3	141.1	80	61
<i>7-Day Strength</i>	<i>28-Day Strength</i>	<i>-Day Strength</i>	<i>56-Day Strength</i>	<i>-Day Strength</i>
3750	4420			
	5000			
Average:	Average:	Average:	Average:	Average:
3750	4710			
Break Date:	Break Date:	Break Date:	Break Date:	Break Date:
9/24/2020	10/15/2020			

Remarks:
 28 Day Results

Specifications: 4500 PSI, 4" Max Slump, 4.5-7.5% Air	Break Sequence: 1@7, 2@28, 1@hold
Summary Comments: Ideal Concrete, Action Ready Mix	



Reviewed By: *R.P.J.*