



ENTECH
 ENGINEERING, INC.
 505 Elkton Drive
 Colorado Springs, CO 80907
 (719) 531-5599 • (719) 531-5238 (fax)

Client:	FLRD #6
Project:	Forest Lakes Residential Development, Filing 6
Entech Job #	201326

CONCRETE TEST

CH			Test #:	7		
Date:	# of Specimens	Specified Strength (psi)	Time of Test	Hours Field Cured	Lab Receive Date:	
11/4/2021	4	4000	9:00 AM	48	11/6/2021	
Specimen Type		Test Type		Type of Cure		
Cylinders 4x8		Field		Lab		
Contractor:		Supplier:		Mix Design Number		
Trax Construction		Transit Mix		T34592110		
Truck Number		Ticket Number		Batch Time:		
35		86485869		8:02 AM		

Location:
 Curb & Gutter; GPS Coordinates: (39.065225° N, 104.911471° W)

Slump (in.):	Air (%):	Unit Weight (PCF):	Concrete Temp (°F)	Air Temp (°F)
1.5	6.4	141.2	74	32

7-Day Strength	28-Day Strength	-Day Strength	56-Day Strength	-Day Strength
5270	5560			
	5610			
	5840			
Average:	Average:	Average:	Average:	Average:
5270	5640			
Break Date:	Break Date:	Break Date:	Break Date:	Break Date:
11/11/2021	12/2/2021			

Remarks:
 28 Day Results

Specifications:	Break Sequence:
4000 PSI, 5" Max Slump, 3-5% Air	1@7, 3@28

Summary Comments:
 Trax Construction, Transit Mix

Reviewed By: *[Signature]*

