

Client:	FLRD #6	
Project: Forest Lakes	Residential Development,	Filing 6
Entech Job #	201326	

CONCRETE TEST										
J. Barnhart			Test #: 29							
Date: #	of Specimens	Specified	Strength (psi)	Time of Test	Н	ours Field Cured	Lab Receive Date:			
6/17/2022	4		4500	9:30	AM	24				
Specimen Type		Test Type		Туре		Type of Cure				
Cylinders 4x8		Field			Lab					
Contractor:		Supplier:				Mix Design Number	•			
Trax Construction		Transit Mix		T34592110						
Truck Number		Ticket Number			Batch Time:					
	73			86703	3512		8:05 AM			
Location:		1			-					
Slump (in.):	Air (%):		Unit Weight (F	PCE).	Concret	e Temp (°F)	Air Temp (°F)			
2.		4.8	Orac Worghi (i	142.7	Concret	82 .e remp(1)	81			
7-Day Strengt	h 28-Day Str	ength	-Da	y Strength	56-L	Day Strength	-Day Strength			
5620										
				-						
Average:	Average:		Average:		Average	<u></u>	Average:			
5620						•	, wordgo,			
Break Date:	Break Date:		Break Date:		Break D	ate:	Break Date:			
6/24/2022	7/15/202	7/15/2022								
Remarks: 7 Day Results.		- <del></del>								
Specifications:				Break Sequence	e:		Ta Ta			
4000 PSI, 5-8% Air			1@7, 3@28							
Summary Comments:										
Trax Construction, Transit Mix										

Reviewed By: