

Client: Proterra Properties

Project: Winsome, LLC

Entech Job # 202064

CONCRETE TEST								
J. Barnhart				Test #: 11				
Date: # o	Specimens	Specified	Strength (psi)	Time of Test	Н	ours Field Cured	Lab Receive Date:	
7/21/2021	4		4500	12:45	PM	24	7/22/20	21
Specimen Type		Test Type				Type of Cure		
Cylinder	Field				Tank			
Contractor:		Supplier:				Mix Design Numbe	r	
Terra Builders		Martin Mariett			ietta		ZCD419	95
Truck Number		Ticket Number				Batch Time:		
1751		68112290			2290	11:29 AM		
Location:		1						
Slump (in.):	Air (%):		Unit Weight (I	PCF):	Concret	e Temp (°F)	Air Temp (°F)	
3.0		5.5		141.6		78	3	36
7-Day Strength	28-Day St	28-Day Strength		-Day Strength		Day Strength	-Day Stren	gth
3910								_
Average:	Average:		Average:		Average	ə:	Average:	
3910								
Break Date:	Break Date:		Break Date:		Break D	Pate:	Break Date:	
7/28/2021	8/18/20	8/18/2021						
Remarks: 7 Day Results								
4500 PSI, 4" Max Slump, 5-8% Air Summary Comments:				Break Sequence: 1@7, 3@28				
Terra Builders, M	lartin Marietta							

Reviewed By: